
PRODUCT DESCRIPTION

Vulkem®360NF/Epoxy WC/346 is a polyurethane traffic deck coating system featuring an epoxy wear course. It is composed of a base coat (360NF), heavy duty, aggregate loaded, intermediate coat (Epoxy WC) and a top coat (346). This unique waterproofing system is designed to have tenacious adhesion, extreme impact and abrasion resistance along with remarkable chemical stability. The elastomeric properties of the system's components enable the complete assembly to give and work with the concrete slab, bridging the shrinkage cracks.

Vulkem 360NF Base Coat is a low-odor, low-VOC, water-cured, rapid setting urethane membrane that bonds firmly to clean, dry concrete and metal. It retains its integrity even if substrate movement causes hair-line cracks of up to 1/16" (1.5 mm). If cut or damaged, Vulkem 360NF will prevent water migration between itself and the substrate.

Vulkem Epoxy WC is a two-part, (1:1) high solids, low odor, VOC compliant, epoxy wear coat applied after the Vulkem 360NF Base Coat has cured. The intermediate coat is loaded with aggregate to give the system excellent impact and abrasion resistance.

Vulkem 346 Top Coat is an aliphatic one-component polyurethane that is applied after the Vulkem Epoxy WC intermediate coat has cured. Interlaminar adhesion to Vulkem Epoxy WC is exceedingly strong. The top coat affords excellent abrasion resistance, UV stability and chemical resistance to complete this Vulkem Traffic Deck Coating System.

BASIC USES

Vulkem 360NF/Epoxy WC/346 is a cold-applied traffic deck coating system designed for waterproofing concrete slabs and protecting occupied areas underneath from water damage. Additionally, the system will protect the concrete from the damaging effects of water, deicing salts, chemicals, gasoline, oils and anti-freeze. It is ideal for high volume traffic areas.

FEATURES & BENEFITS

- Mildew and fungus resistance safeguards concrete surfaces against environmental contaminants.
- Excellent durability and UV resistance extends the useful life of vehicular systems.
- Superior aggregate retention.
- Recoatable and compatible with other Tremco sealants and expansion joints, which enhance waterproofing protection with full system compatibility.

AVAILABILITY

Immediately available from your local Tremco Sales Representative, Tremco distributor, or warehouse.

PACKAGING

Vulkem 360NF: 5 gal (18.9 L) in a 6-gal (22.7-L) pail.

Vulkem Epoxy WC: 10-gal (37.9-L) kit—Part A: 1 5-gal (18.9-L) pail, Part B: 1 5-gal (18.9-L) pail.

Vulkem 346: 5-gal (18.9-L) pails, 55-gal (208-L) drums.

COLORS

Vulkem 346 is available in Gray, Limestone, Slate Gray, *Black, *White, *Beige, and *Maple. Made-to-order and special colors also are available upon request.

*Denotes special color.

INSTALLATION

Concrete shall be water-cured and attain a 4000 psi minimum compressive strength. Concrete finish shall be a light steel trowel followed by a fine-hair broom, or equivalent ICRI #3-#4 finish. Moisture content in the concrete must be lower than 4.5% as measured by a Tramex CME 4 Moisture Meter. Depending on concrete construction and job site location, additional concrete testing may be required. Please contact your local Tremco Sales or Technical Representative. Please refer to the Vulkem360NF/Epoxy WC/346 Application Instructions for complete application details. The techniques involved may require modification to adjust to the jobsite conditions. Consult your Tremco Sales Representative or Tremco Technical Service for site conditions and requirements.

APPLICABLE STANDARDS

Conforms to:

- ASTM C957
- CSA S413-14
- Conforms to UL 790 - Class A Fire Rating for non-combustible substrates

LIMITATIONS

- Do not apply to damp or contaminated surfaces.
- Use with adequate ventilation.
- Substrate must be at least 5°F (3°C) above the measured dew point temperatures to avoid dew point conditions.

WARRANTY

A repair or replacement warranty is available on all Tremco products. Visit <https://www.tremcosealants.com/warranties/> for details.

TYPICAL PHYSICAL PROPERTIES

PROPERTY	TEST METHOD	VULKEM 360NF	VULKEM EPOXY WC	VULKEM 346
Flash Point	Set-A-Flash	185 °F (85 °C)	>200 °F (93 °C)	85 °F (29 °C)
% Solids (by Weight)	ASTM D1353	91%	100%	72%
Drying Time @ 75F, 50% RH	ASTM D1640	25 mil film, 6	12 mil film, 10 ± 2 hr	10 - 12 mil film, 6 to 8 hr
Open to vehicular traffic		N/A	N/A	72 hr after cure
Weathering	ASTM D822	N/A	N/A	No Effect
Salt Spray	ASTM B117	N/A	N/A	No Effect
Viscosity	Brookfield C&P	8000 to 10000 cps	300 to 400 cps	2000 to 3000 cps
Elongation	ASTM D412	500%	30%	120%
Tensile Strength	ASTM D412	275 psi	3000 psi	2800 psi
Hardness (Shore A)	ASTM D2240	40 to 50	72 (Shore D)	85 to 95
Adhesion (Pull Off)	ASTM D4541	350 psi	N/A	N/A
Abrasion Resistance (1000 Cycles)	ATSM D4060	N/A	N/A	50 mg
Accelerated Aging	ASTM D573	No loss of elongation or tensile strength	No loss of elongation or tensile strength	No loss of elongation or tensile strength
Adhesion (Peel Strength)	ASTM D903	Unprimed concrete, 45 pli, 100% cohesive failure	100% cohesive failure	100% cohesive failure
Tear Strength	ASTM D624	N/A	330 pli	370 pli

*Accelerated aging test. 1 daily cycle of UV and water spray greatly exceeds 1 day of real-world exposure. Contact Tremco Technical Service or your local sales representative for more information.

Please refer to our website at www.tremcosealants.com for the most up-to-date Product Data Sheets.

NOTE: All Tremco Safety Data Sheets (SDS) are in alignment with the Globally Harmonized System of Classification and Labelling of Chemicals (GHS) requirements

360NFEWC346-DS/0323

Tremco Construction Products Group (CPG) brings together the Commercial Sealants & Waterproofing and Roofing & Building Maintenance divisions of Tremco CPG Inc.; Dryvit and Willseal brands; Nudura Inc.; Prebuck LLC; Tremco Barrier Solutions, Inc.; Weatherproofing Technologies, Inc.; Weatherproofing Technologies Canada, Inc.; and Pure Air Control Services, Inc.



tremcosealants.com | 800.321.7906



Construction Products Group

3735 Green Rd. | Beachwood, OH 44122
800.321.7906 | tremcocpg.com