

We certify that Tremco Permaquik 200 Crystalline has been tested against the following ASTM methods and does conform to the specification requirements.

Physical Properties	Typical Values		Test Method
Hydrostatic Head Pressure	100' (28 m)		
Compressive Strength	Days	PSI	ASTM C39
	3	4145	
	7	5560	
	28	6970	
Water Permeability	6.6 x 10 ⁻¹² K, cm/sec		ASTM-D 5084
Water Vapor Transmission	.012 perms		ASTM E96