

## CERTIFICATION LETTER

We certify that TREMproof® 560A has been tested to the following typical physical properties:

PROPERTY	TEST METHOD	TYPICAL RESULTS
Thickness		60 mil (1.5 mm)
Dimensions		39" x 67' (1 x 20.4 m)
Surface		Cross-laminated polyethylene
Service Temperature		-4°F to 167°F (-20°C to 75°C)
Application Temperature		41°F to 113°F (5°C to 45°C)
Tensile Strength, MD/XD	ASTM D822	45/48 N/mm <sup>2</sup>
Elongation (Film), MD/XD	ASTM D822	230/200 %
Low Temperature Flexibility	ICC AC48	Pass
Water Absorption	ASTM D570	<0.1
Water Vapor Permeance	ASTM E96	Procedure B: <0.01 perms
Crack bridging ability, 100 cycles, @ -26 °F (-32°C)	ASTM C1305	Pass
Resistance to hydrostatic head	ASTM D5385	Pass
Adhesion to primed concrete	ASTM D1000	7 lbs./in

Tremco Incorporated and its facilities are also certified to ISO 9001:2000