

Product Description

Vulkem® 360NF/950NF/950NF is a modified polyurethane traffic deck coating system composed of a base coat (360NF), heavy duty intermediate coat (950NF) and a top coat (950NF). This unique waterproofing system is designed to have tenacious adhesion, extreme impact and abrasion resistance along with remarkable chemical stability. The elastomeric properties of the system's components enable the complete assembly to give and work with the concrete slab, bridging the shrinkage cracks.

Vulkem 360NF Base Coat is a low-odor, low-VOC, water-cured, rapid setting urethane membrane that bonds firmly to clean, dry concrete and metal. It retains its integrity even if substrate movement causes hair-line cracks of up to 1/16" (1.5 mm). If cut or damaged, Vulkem 360NF will prevent water migration between itself and the substrate.

Vulkem 950NF Intermediate Coat is a low VOC, two-component urethane that is applied after the Vulkem 360NF Base Coat has cured. The intermediate coat is loaded with aggregate to give the system excellent impact, abrasion and chemical resistance.

Vulkem 950NF Top Coat is a two-component polyurethane that is applied after the Vulkem 950NF intermediate coat has cured. Interlaminar adhesion to Vulkem 950NF is exceedingly strong. The top coat affords excellent abrasion resistance and chemical resistance to complete this Vulkem Traffic Deck Coating System.

Basic Uses

Vulkem 360NF/950NF/950NF is a cold-applied traffic deck coating system designed for waterproofing concrete slabs and protecting occupied areas underneath from water damage. Additionally, the system will protect the concrete from the damaging effects of water, deicing salts, chemicals, gasoline, oils and anti-freeze.

Features and Benefits

- Fast cure through time allows for use 24 hr after installation.
- Low odor and low level of Volatile Organic Compounds (VOC) provides for use in neighbor friendly, inhabited structures.
- Mildew and fungus resistance safeguards concrete surfaces against environmental contaminants.
- Excellent durability extends the useful life of vehicular systems. Ideal for indoor parking structures.
- Recoatable and compatible with other Tremco sealants, which enhance waterproofing protection with full system compatibility.

Availability

Immediately available from your local Tremco Sales Representative, Tremco distributor, or warehouse.

Packaging

Vulkem 360NF: 5 gal (18.9 L) in a 6-gal (22.7-L) pail.

Vulkem 950NF: Total of 4.2-gal kit - Part A 3.25-gal (12.3 L) in a 5-gal (18.9-L) pail, Part B 0.95 gal (3.6 L) in a 1-gal pail.

Colors

Vulkem 950NF is available in Gray, Slate Gray, and Black. Made-to-order and special colors also are available upon request.

Fire Rated Assemblies

- ANSI/UL790 - Standard Test Methods for Fire Tests of Roof Coverings
- CAN/ULC-S107 - Methods of Fire Tests of Roof Coverings

Installation

Concrete shall be water-cured and attain a 4000 psi minimum compressive strength. Concrete finish shall be a light steel trowel followed by a fine-hair broom, or equivalent ICRI #2-#4 finish. Moisture content in the concrete must be lower than 4.5% as measured by a Tramex CME 4 Moisture Meter.

Depending on concrete construction and job site location, additional concrete testing may be required. Please contact your local Tremco Sales or Technical Representative.

Please refer to the Vulkem 360NF/950NF/950NF Application Instructions for complete application details. The techniques involved may require modification to adjust to the jobsite conditions. Consult your Tremco Sales Representative or Tremco Technical Service for site conditions and requirements.

Applicable Standards

Conforms to ASTM C957

Limitations

- Do not apply to damp or contaminated surfaces.
- Use with adequate ventilation.

Warranty

Tremco warrants its Products to be free of defects in materials but makes no warranty as to appearance or color. Since methods of application and on-site conditions are beyond our control and can affect performance, Tremco makes no other warranty, expressed or implied, including warranties of MERCHANTABILITY and FITNESS FOR A PARTICULAR PURPOSE with respect to Tremco Products. Tremco's sole obligation shall be, at its option, to replace or to refund the purchase price of the quantity of Tremco Products proven to be defective, and Tremco shall not be liable for any loss or damage.

Please refer to our website at www.tremcosealants.com for the most up-to-date Product Data Sheets.

NOTE: All Tremco Safety Data Sheets (SDS) are in alignment with the Globally Harmonized System of Classification and Labelling of Chemicals (GHS) requirements.

Vulkem® 360NF/950NF/950NF

Elastomeric, Waterproof Indoor Traffic Deck Coating System

TYPICAL PHYSICAL PROPERTIES

| PROPERTY | TEST METHOD | VULKEM 360NF | VULKEM 950NF | VULKEM 950NF |
|-----------------------------------|----------------|--|---|---|
| Flash Point | Set-A-Flash | 185 °F (85 °C) | 200 °F (93 °C) | 200 °F (93 °C) |
| % Solids (by Weight) | ASTM D1353 | 91% | 99% | 99% |
| Drying Time @ 75 °F, 50% RH | ASTM D1640 | 25 mil film, 6 to 12 hr | 12 mil film, 2 to 4 hr | 12 mil film, 2 to 4 hr |
| Open to vehicular traffic | | N/A | N/A | 24 hr after cure |
| Weathering | ASTM D822 | N/A | N/A (Indoor use only) | N/A (Indoor use only) |
| Salt Spray | ASTM B117 | N/A | No effect | No effect |
| Viscosity | Brookfield C&P | 8000 to 10000 cps | 2000 cps | 2000 cps |
| Elongation | ASTM D412 | 500% | 100% | 100% |
| Tensile Strength | ASTM D412 | 275 psi | 4200 psi | 4200 psi |
| Hardness (Shore A) | ASTM D2240 | 40 to 50 | 75 shore D | 75 shore D |
| Adhesion (Peel Strength) | ASTM D903 | Unprimed concrete, 45 pli, 100% cohesive failure | 100% cohesive failure | 100% cohesive failure |
| Adhesion (Pull-Off) | ASTM D4541 | 350 psi | N/A | N/A |
| Abrasion Resistance (1000 cycles) | ATSM D4060 | N/A | 70 mg | 70 mg |
| Accelerated Aging | ASTM D573 | No loss of elongation or tensile strength | No loss of elongation or tensile strength | No loss of elongation or tensile strength |

* Accelerated aging test. 1 daily cycle of UV and water spray greatly exceeds 1 day of real world exposure. Contact Tremco Technical Service or your local sales representative for more information.

0319/360NF/950NF/950NFDS-DC

Please refer to our website at www.tremcosealants.com for the most up-to-date Product Data Sheets.

**Tremco Commercial Sealants & Waterproofing**

3735 Green Rd
Beachwood OH 44122
216.292.5000 / 800.321.7906

1451 Jacobson Ave
Ashland OH 44805
419.289.2050 / 800.321.6357

220 Wicksteed Ave
Toronto ON M4H1G7
416.421.3300 / 800.363.3213

1445 Rue de Coulomb
Boucherville QC J4B 7L8
514.521.9555