



TECHNICAL DATA SHEET

VULKEM® 950NF

Two Component Neighbor Friendly
Polyurethane Intermediate or Top Coat

PRODUCT DESCRIPTION

Vulkem 950NF is an aromatic, low VOC, two-component polyurethane, intermediate or top coat which when used in conjunction with the recommended aggregate, creates a tough, aesthetically appealing, skid resistant, wearing surface that forms a strong interlaminar bond to the base coat.

BASIC USES

Vulkem 950NF is ideal for pedestrian, vehicular decks, mechanical rooms and similar applications requiring an elastomeric waterproofing system.

AVAILABILITY

Immediately available from your local Tremco Sales Representative, Tremco Distributor or Tremco Warehouse.

PACKAGING

Vulkem 950NF: Total of 4.2-gal kit—Part A 3.25 gal (12.3 L) in a 5-gal (18.9-L) pail, Part B 0.95 gal (3.6 L) in a 1-gal pail.

COLORS

Vulkem 950NF is available in Gray, Slate Gray, Black, Charcoal, *White, *Beige, *Limestone and *Maple. Made-to-order and special colors are also available upon request.

*Denotes special color.

LIMITATIONS

- Do not apply to damp or contaminated surfaces.
- Use with adequate ventilation.

INSTALLATION

Refer to the instructions for your specific system/application for installation details. The techniques involved may require modification to adjust to jobsite conditions. Consult your Tremco Representative for specific design requirements.

WARRANTY

A repair or replacement warranty is available on all Tremco products. Visit <https://www.tremcosealants.com/warranties/> for details.

TYPICAL PHYSICAL PROPERTIES

PROPERTY	TEST METHOD	VULKEM 950NF
Flash Point	Set-A-Flash	200 °F (93 °C)
% Solids (by Weight)	ASTM D1353	99%
Drying Time @ 75 °F, 50% RH	ASTM D1640	12 mil film, 2 to 4 hr
Weathering	ASTM D822	N/A
Salt Spray	ASTM B117	N/A
Viscosity	Brookfield C&P	2000 cps
Elongation	ASTM D412	100%
Tensile Strength	ASTM D412	4200 psi
Hardness (Shore A)	ASTM D2240	75
Adhesion (Peel Strength)	ASTM D903	100% cohesive failure
Adhesion (Pull-Off)	ASTM D4541	N/A
Abrasion Resistance (1000 cycles)	ASTM D4060	70 mg
Accelerated Aging	ASTM D573	No loss of elongation or tensile strength

* Accelerated aging test. 1 daily cycle of UV and water spray greatly exceeds 1 day of real world exposure. Contact Tremco Technical Service or your local sales representative for more information.

Please refer to our website at www.tremcosealants.com for the most up-to-date Product Data Sheets.

NOTE: All Tremco Safety Data Sheets (SDS) are in alignment with the Globally Harmonized System of Classification and Labelling of Chemicals (GHS) requirements.

V950NF-DS/0323

Tremco Construction Products Group (CPG) brings together Tremco CPG Inc. and its Dryvit and Nudura brands; Willseal; Prebuck LLC; Tremco Barrier Solutions, Inc.; Weatherproofing Technologies, Inc. and its Pure Air Control Services and Canam Building Envelope Specialists offerings; and Weatherproofing Technologies Canada, Inc.



tremcosealants.com | 800.321.7906



Construction Products Group

3735 Green Rd. | Beachwood, OH 44122
800.321.7906 | tremcocpg.com