

---

## Product Description

Vulkem® EWS with PUMA Technology is designed to have tenacious adhesion and extreme abrasion resistance. It can be walked on in one hour, which will minimize operation disruption. Vulkem Extreme Wearing System (EWS) is a waterproof traffic deck coating system that utilizes polyurethane-methacrylate (PUMA) technology. Vulkem EWS vehicular system is composed of a primer (Tremco PUMA Primer of TREMprime VB Primer), a base coat (Tremco PUMA BC), an intermediate wear coat (Tremco PUMA WC) and a top coat (Tremco PUMA TC). All system components are cured using Tremco PUMA Initiator.

Tremco PUMA Primer is a methyl-methacrylate (MMA), two-component primer for porous and non-porous substrates.

TREMprime VB Primer is a two-component, epoxy-based, solvent-free vapor barrier primer for concrete and plywood surfaces.

Tremco PUMA BC is a modified polyurethane-methacrylate (PUMA) base coat. Tremco PUMA BC bonds firmly to Tremco PUMA Primer. It retains its integrity even if substrate movement causes hair-line cracks of up to 1/16" (1.5 mm). If cut or damaged, Tremco PUMA BC will prevent water migration between itself and the substrate.

Tremco PUMA WC is a modified polyurethane-methacrylate (PUMA) wear coat. Tremco PUMA WC is applied after Tremco PUMA BC has cured. The wear coat is loaded with aggregate to give the system excellent impact, abrasion and chemical resistance. Tremco PUMA TC is a methyl-methacrylate (MMA) top coat. Interlaminar adhesion to Tremco PUMA TC is exceedingly strong. The top coat affords excellent abrasion resistance, UV stability and chemical resistance to complete the Vulkem EWS vehicular system.

---

## Basic Uses

Vulkem EWS is a cold-applied traffic deck coating system designed for waterproofing concrete slabs and protecting occupied areas underneath from water damage. Additionally, the system will protect the concrete from the damaging effects of chloride, deicing salts, chemicals, gasoline, oils and anti-freeze. The Vehicular System is ideal for ramps, helical turns and ticket splitters.

---

## Features and Benefits

- Polyurethane-methacrylate (PUMA) technology delivers extreme durability while maintaining its crack-bridging characteristics.
- Rapid set-up times allow for quick overall installation, as well as the ability to open up to foot traffic one hour later.
- Can be applied at temperatures below 20° F (-7° C), which allows for continuation of projects in the colder months.
- Initiator adjustments allow for 30 to 45 min cure time between applications, even at temperatures below freezing.
- Compatible with Tremco sealants and coatings, which is essential for tie-ins, detailing and penetrations.
- Extremely forgiving application allows users to apply additional coats long after the previous coat has cured.
- Unique chemistry allows for easy repair.

---

## Availability

Immediately available from your local Tremco Sales Representative

---

## Applicable Standards

ASTM C957  
CSA S413

---

## Packaging

Tremco PUMA Primer: 6-gal pails

TREMprime VB Primer: Part A: 2.4-gal pails  
Part B: 1.2-gal pails

Tremco PUMA BC: 6-gal pails

Tremco PUMA WC: 6-gal pails

Tremco PUMA TC: 6-gal pails

Tremco PUMA Initiator: 22-lb bags in 2-gal pails  
55-lb bags in 6-gal pails

Tremco PUMA Filler Powder: 55-lb bags

Tremco PUMA Cleaner: 6-gal pails

---

## Colors

Tremco PUMA TC is available in Gray, Slate Gray, White, Tintable and Decorative.

---

## Installation

Concrete shall be water-cured and attain a 4000 PSI minimum compressive strength. Concrete finish shall be a light steel trowel followed by an equivalent ICRI #3-#4 finish. Moisture content in the concrete must be lower than 6% as measured using a Tramex CME 4 Moisture Meter. Depending on concrete construction and job site location, additional concrete testing may be required. Please contact your local Tremco Sales or Technical representative.

Please refer to the Vulkem EWS Application Instructions for complete application details. The techniques involved may require modification to adjust to job-site specific conditions. Consult your Tremco Sales Representative or Tremco Technical Services for site conditions and requirements.

---

## Limitations

- Do not apply to damp or contaminated surfaces.
- Use with adequate ventilation.

---

## Warranty

Tremco warrants its Products to be free of defects in materials but makes no warranty as to appearance or color. Since methods of application and on-site conditions are beyond our control and can affect performance, Tremco makes no other warranty, expressed or implied, including warranties of MERCHANTABILITY and FITNESS FOR A PARTICULAR PURPOSE with respect to Tremco Products. Tremco's sole obligation shall be, at its option, to replace or to refund the purchase price of the quantity of Tremco Products proven to be defective, and Tremco shall not be liable for any loss or damage.

## Vulkem® EWS with PUMA Technology (Vehicular)

Waterproof Traffic Coating System-Vehicular System Ready for Use 1 Hour After Application

Please refer to our website at [www.tremcosealants.com](http://www.tremcosealants.com) for the most up-to-date Product Data Sheets.

NOTE: All Tremco Safety Data Sheets (SDS) are in alignment with the Globally Harmonized System of Classification and Labelling of Chemicals (GHS) requirements.

### TYPICAL PHYSICAL PROPERTIES

| PROPERTY                          | TEST METHOD                    | TREMCO PUMA BC (All Grades)  | TREMCO PUMA WC    | TREMCO PUMA TC    |
|-----------------------------------|--------------------------------|------------------------------|-------------------|-------------------|
| Flash Point                       | Set-A-Flash                    | 53°F                         | 53°F              | 53°F              |
| VOC Content                       | Method 310                     | 0 g/L                        | 0 g/L             | 0 g/L             |
| % Solids (by Weight)              | ASTM D1353                     | 100%                         | 100%              | 100%              |
| Drying Time @ 75°F, 50% RH        | ASTM D1640                     | 80 mil film, 1 hr            | 65 mil film, 1 hr | 17 mil film, 1 hr |
| Weathering                        | ASTM D822 Weatherometer 350 hr | N/A                          | N/A               | No effect         |
| Elongation                        | ASTM D638                      | 407% - 420%                  | 250%              | 130%              |
| Elongation                        | ASTM D5147                     | Min 30%                      | Min 30%           | Min 30%           |
| Tensile Strength                  | ASTM D638 @ 75°F               | 991 - 1680 psi               | 1550 psi          | 986 psi           |
| Tearing Resistance                | ASTM D4073                     | 91 lbf                       | 148 lbf           | 203 lbf           |
| Hardness (Shore D)                | ASTM D2240                     | 18 - 35                      | 45                | 55                |
| Hardness (Shore A)                | ASTM D2240                     | 65 - 87                      | 96                | 100               |
| Abrasion Resistance (1000 cycles) | ATSM D4060                     | N/A                          | N/A               | 51 mg             |
| Low-Temperature Crack Bridging    | ASTM C1305                     | Passes                       | N/A               | N/A               |
| Taber Abrasion                    | ASTM C501                      | Passes                       | N/A               | N/A               |
| Peak Load @ 73°F, avg.            | ASTM D5147                     | >70 lbf/in                   | 81 lbf/in         | 238 lb/in         |
| Puncture Resistance               | ASTM D5602                     | > 56 lbs                     | > 56 lbs          | >56 lbs           |
| Water Absorption                  | ASTM D570                      | < 0.1%                       | < 0.1%            | < 0.1%            |
| Water Vapor Transmission          | ASTM E96                       | 0.03 perms                   | 0.03 perms        | 0.03 perms        |
| Adhesion-in-Peel                  | ASTM C794                      | Concrete failure with primer | 35 lbs            | N/A               |
| Self-Ignition Temperature         | ASTM D1929                     | 800° F<br>427° C             | 840° F<br>449° C  | 850° F<br>454° C  |
| Smoke Density                     | ASTM D2843                     | 4.1%                         | 28.7%             | 2.1%              |
| Rate of Burn                      | ASTM D635                      | 1.2 in/min                   | 1.7 in/min        | 0.2 in/min        |

#### 0519/ EWSVDS-DC

#### Tremco Commercial Sealants & Waterproofing

3735 Green Rd  
Beachwood OH 44122  
216.292.5000 / 800.321.7906

1451 Jacobson Ave  
Ashland OH 44805  
419.289.2050 / 800.321.6357

220 Wicksteed Ave  
Toronto ON M4H1G7  
416.421.3300 / 800.363.3213

1445 Rue de Coulomb  
Boucherville QC J4B 7L8  
514.521.9555

