

TUFF-N-DRI® XTS

Performance-Engineered and Field-Tested

Product Overview

TUFF-N-DRI® XTS is the highest performing extension of the most recognized waterproofing brand in the residential new construction market, with 12 feet of hydrostatic head pressure resistance! TUFF-N-DRI XTS is performance-engineered and field-tested to provide the greatest resistance to hydrostatic head pressure of any polymer-modified asphalt emulsion waterproofing membrane in the category. Now, TUFF-N-DRI XTS is designed to withstand 12 feet of hydrostatic head pressure, while maintaining its ease of use, consistency of manufacture and long-term durability characteristics.



Features & Benefits

20-Year Warranty

With up to a 20-year performance warranty, TUFF-N-DRI XTS delivers guaranteed dry basements, increasing the comfort and utility of your lower-level living space.

Availability and Cost.

TUFF-N-DRI XTS is competitively priced and available through your local Tremco Contractor. For details, contact your local Tremco Contractor, call 800-DRY-BSMT or visit tuff-n-dri.com.

Up to 12 times more hydrostatic head resistance than the competition!



MEMBRANE PROPERTIES

Type: Polymer-enhanced asphalt liquid-applied membrane	
Color: Black	
Solids: 64% ± 3% (percent by weight)	
Density: 8.1 ± .15 lbs/gal	
Application: Airless spray	
Application Temperature: Minimum 20°F	
Application Thickness: 60 mils (wet) ¹	
Typical Cure Time: 16–24 hrs (under normal conditions)	
Hydrostatic Head Resistance Results: 12 ft.	Method: ASTM D-5385
Adhesion to Concrete: (Peel, N/m) Results: Exceeds	Method: ASTM C-836
Elongation Results: >1800%	Method: ASTM D-412
Crack Bridging Ability Results: Passes	Method: ASTM D-836
Water Vapor Permeance Results: <1 perm for 40-mil dry coating (grains/sf/hr)	Method: ASTM E-96 Wet Method
Tensile Strength Results: 70 PSI	Methods: ASTM D-412
Resistance to Degradation in Soil Results: Good	Method: ASTM E-154
Mold Growth and Bacterial Attack Results: No Degradation	Methods: ASTM D-3273, ASTM D-3274

¹ Measured in-place with an ASTM D-4414 notch film gauge. Wet film measuring 60 mils cures to 40 dry mils.

Tremco Commercial Sealants & Waterproofing | 3735 Green Road | Beachwood, OH 44122 | US: 800.852.9068 | CAN: 800.363.3213 | tremcosealants.com

Tremco Construction Products Group (CPG) brings together Tremco Incorporated's Commercial Sealants & Waterproofing and Roofing & Building Maintenance operating divisions; Dryvit Systems, Inc.; Nudura Inc.; Willseal; Weatherproofing Technologies, Inc. and Weatherproofing Technologies Canada, Inc.



Tremco® and TUFF-N-DRI® are registered trademarks of Tremco Incorporated.
Use of the ® symbol indicates registration with the US Patent & Trademark Office and the Canadian Intellectual Property Office.

1220/TNDXTSSS

tremcocpg.com