

Tremco® Reemay

Reinforcing Fabric 2014

Product Description

A spunbund polyester fabric style 2014, consisting of a nonwoven fabric of continuous filament polyester fibers that are randomly arranged. These fibers are highly dispersed and thermally bonded at the filament junctions.

Basic Uses

Tremco® Reinforcing Fabric is used to reinforce fluid-applied membranes in multi-lift applications.

Packaging

84 in. x 675 ft. (2.13m x 206m) roll

36 in. x 600 ft. (0.91m x 183m) roll

12 in. x 600 ft. (30cm x 183m) roll

6 in. x 600 ft. (15cm x 183m) roll

Warranty

Tremco warrants its Products to be free of defects in materials, but makes no warranty as to appearance or color. Since methods of application and on-site conditions are beyond our control and can affect performance, Tremco makes no other warranty, expressed or implied, including warranties of MERCHANTABILITY and FITNESS FOR A PARTICULAR PURPOSE. With respect to Tremco Products, Tremco's sole obligation shall be, at its option, to replace or refund the purchase of the quantity of material proved to be defective and Tremco shall not be liable for any loss.

Please refer to our website at www.tremcosealants.com for the most up-to-date Product Data Sheets.

TYPICAL PHYSICAL PROPERTIES

Properties	Test Method	Results
Color	—	White
Weight	—	1.00 oz/y ²
% Elongation (to break)	ASTM D 2523	—
Tear Strength	ASTM D 2263	—
Breaking Strength (lb.)	ASTM D 2523	—
De Matia Flex Cycles	ASTM D 813	—
Thickness (mil)	—	9 mil
Sheet Grab Tensile (lbs - MD x XD)	ASTM D 2523	21 lbs. x 17 lbs.
Trapezoid Tear (lbs - MD x XD)	ASTM D 2263	6 lbs. x 11 lbs.
Mullen Burst (psi)	ASTM D 2523	22 psi



Tremco Commercial Sealants & Waterproofing

3735 Green Road, Beachwood, OH 44122 // Phone: 216.292.5000 // 800.321.7906

220 Wicksteed Avenue, Toronto, ON M4H 1G7 // Phone: 416.421.3300 // 800.363.3213

1451 Jacobson Avenue, Ashland OH 44805 // Phone: 419.289.2050 // 800.321.6357