

Tremco Incorporated certifies that TREMDrain 6000 multi-composite drainage and protection boards meet the physical properties outlined in the Tremco Incorporated published data sheets, specifications, and application instructions. This product has been tested against the following ASTM methods as shown herein:

TREMDrain® 6000

Multi-Composite Drainage and Protection Boards

TYPICAL PHYSICAL PROPERTIES

PROPERTY	TEST METHOD	VALUES US	VALUES SI
Typical Applications			
Flow Capacity per unit width	ASTM D4716	18 gpm/ft	224 Lpm/M
Roll Length		50'	15.24 M
Roll Width		6'	1.8 M
Fabric			
Material		Polypropylene	
Weight	ASTM D3776		
Grab Tensile Strength	ASTM D4632	115 lbf	512 N
Puncture Strength	ASTM D4833	70 lb	311 N
Trapezoidal Tear	ASTM D4533		
Mullen Burst Strength	ASTM D3786		
Grab Elongation	ASTM D4632	70%	
AOS	ASTM D4751	70 sieve	0.21 mm
Flow Rate	ASTM D4491	150 gpm/ft ²	6,6116 Lpm/M ²
Root Barrier Fabric		None	
UV Resistance	ASTM D4355	70% / 500 hr	
Core			
Material		Polypropylene	
Thickness	ASTM D1777	0.4"	
Compressive Strength		15,000 lb/ft ²	718 kPa