

CERTIFICATION LETTER

Tremco Incorporated certifies that the Vulkem[®] 350FC/951NF/951NF Vehicular Deck Coating System meets the following typical physical properties per the Tremco Incorporated published data sheets, specifications, and application instructions.

The following pertain to the Vulkem 350FC/951NF/951NF fluid applied traffic coating system:

| TYPICAL PHYSICAL PROPERTIES | | | | |
|-----------------------------------|----------------|---------------------------|--|--|
| PROPERTY | TEST METHOD | VULKEM 350FC | VULKEM 951NF | VULKEM 951NF |
| % Solids (by weight) | ASTM D1353 | 85% | 80 to 85% | 80 to 85% |
| Drying Time @ 75 °F, 50% RH | ASTM D1640 | 25 mil film, 3 to 4 hr | 12 mil film, 2 to 4 hr | 12 mil film, 2 to 4 hr |
| Open to vehicular traffic | | N/A | 24 hr after cure | 24 hr after cure |
| Weathering | ASTM D822 | N/A | No effect | No effect |
| Salt Spray | ASTM B117 | N/A | No effect | No effect |
| Viscosity | Brookfield C&P | 2500 cP | 2500 cps | 2500 cps |
| Elongation | ASTM D412 | >500% | 145% | 145% |
| Tensile Strength | ASTM D412 | >3500 psi | 4500 psi | 4500 psi |
| Hardness | ASTM D2240 | >90 (Shore A) | 50 (Shore D) | 50 (Shore D) |
| Adhesion-in-Peel | ASTM C794 | >20 pli | N/A | N/A |
| Adhesion (Peel Strength) | ASTM D903 | 30 pli, substrate failure | 100% cohesive failure | 100% cohesive failure |
| Adhesion (Pull-Off) | ASTM D4541 | >500 psi | N/A | N/A |
| Abrasion Resistance (1000 cycles) | ASTM D4060 | N/A | 33 mg | 33 mg |
| Accelerated Aging* | ASTM D573 | N/A | No loss of elongation or tensile strength | No loss of elongation or tensile strength |
| Tear Strength | ASTM D624 | >250 pli | 480 pli | 480 pli |

1/30/2023