

Product Description


Tremco Cellular Rubber Extrusions are fabricated into gaskets and accessories for use in sealing and glazing applications in building construction.

Metal Requirements

Tremco Cellular Rubber Extrusions are manufactured to meet existing metal designs or developed with custom metal systems at the design development stage. Many profiles are available depending upon existing metal requirements.

Availability

Tremco Cellular Rubber Extrusions are generally custom manufactured but many standard designs are available. Their availability and cost may be obtained from your local Tremco representative, or by contacting our Customer Service Department in Ashland, Ohio, at 800-321-6357 or in Canada at 800-323-3213.



Packaging

Tremco Cellular Rubber Extrusions are packaged based on customer requirements, profile size, configuration and the need for molded picture frame gaskets.

Warranty

Tremco warrants its Products to be free of defects in materials but makes no warranty as to appearance or color. Since methods of application and on-site conditions are beyond our control and can affect performance, Tremco makes no other warranty, expressed or implied, including warranties of MERCHANTABILITY and FITNESS FOR A PARTICULAR PURPOSE with respect to Tremco Products. Tremco's sole obligation shall be, at its option, to replace or to refund the purchase price of the quantity of Tremco Products proven to be defective, and Tremco shall not be liable for any loss or damage.

Please refer to our website at www.tremcosealants.com for the most up-to-date Product Data Sheets.

NOTE: All Tremco Safety Data Sheets (SDS) are in alignment with the Globally Harmonized System of Classification and Labelling of Chemicals (GHS) requirements.

TYPICAL PHYSICAL PROPERTIES

PROPERTY	PER ASTM 509 REQUIREMENTS		
	TEST METHOD	FLAME NEOPRENE	STANDARD EPDM
Compression-Deflection 25% Deflection Limits	ASTM D-1056	18-24 psi (124-165 kPa)	19-24 psi (131-165 kPa)
Compression Set, 22 hr @ 158 °F (70 °C)	ASTM D395	22 - 28%	26 - 30%
Ozone Resistance, Type II 300mPa 100 hr @ 104 °F (40 °C) 40% Elongation	ASTM D1149	No Cracks	No Cracks
Water Absorption, % weight	ASTM C1083	2.0 - 3.0%	2.0 - 3.5%
Low-Temperature Brittleness @ -40 °C	ASTM D746	Pass	Pass
Flame Propagation, Option I	ASTM C1166	Pass	-----
Flame Propagation, Option II	ASTM C1166	No Limit	No Limit
Nonstaining	ASTM D925	No migratory stain	No migratory stain

0316/CELLULAR-GL

Tremco Commercial Sealants & Waterproofing

3735 Green Rd
Beachwood OH 44122
216.292.5000 / 800.321.7906

1451 Jacobson Ave
Ashland OH 44805
419.289.2050 / 800.321.6357

220 Wicksteed Ave
Toronto ON M4H1G7
416.421.3300 / 800.363.3213

1445 Rue de Coulomb
Boucherville QC J4B 7L8
514.521.9555

