



# EasyDri™ Crack Seal

Single component polyurethane sealant

## DATA SHEET

### Product Description

EasyDri™ Crack Seal allows basement walls to be treated while they are still wet. Unlike conventional crack injection, which requires the walls be completely dry, EasyDri Crack Seal can be used right away. That means treating more walls sooner without the need to wait. Within only 8 hours of installation, EasyDri provides up to 8 feet of hydrostatic head resistance on the interior walls. This protection continues to strengthen over the next 24 hours as EasyDri cures to its full waterproofing potential, keeping areas free of moisture.

### Features & Benefits

- Quicker – Less than 60 minutes to finish an 8' crack.
- Easier – Installed by one person in half the time as traditional epoxies or urethanes.
- Neater – Smooth, concrete-colored finish, no unsightly ports, no oozing sealants.

Please refer to our website at [www.tremcosealants.com](http://www.tremcosealants.com) for the most up-to-date Product Data Sheets.

**NOTE:** All Tremco Safety Data Sheets (SDS) are in alignment with the Globally Harmonized System of Classification and Labelling of Chemicals (GHS) requirements.

## EASYDRI SEALANT PROPERTIES

PROPERTY	DESCRIPTION	
TYPE	Single component polyurethane sealant	
SOLIDS	98%	
SPECIFIC GRAVITY	1.3302	
TACK FREE TIME	6 to 8 hours, 73°F (23°C), 50% RH	
APPLICATION TEMPERATURE	45°F (7°C) to 100°F (38°C)	
PROPERTY	TEST METHOD	TYPICAL RESULTS
SKIN TIME	ASTM C679	2 to 3 hours
ADHESION TO CONCRETE	ASTM C794	35 pli
ADHESION TO CONCRETE AFTER IMMERSION	ASTM C794	30 pli
ADHESION TO GREEN CONCRETE	ASTM C794	>25 pli
ADHESION TO DAMP CONCRETE	ASTM C794	>20 pli
TENSILE STRENGTH	ASTM D412	350 to 450 psi
ELONGATION	ASTM D412	800% to 900%

## TUFF-N-DRI® H8 Membrane

Liquid-applied membrane

### EASYDRI COATING PROPERTIES

PROPERTY	DESCRIPTION
TYPE	Elastomeric, emulsion based coating
COLOR	Grey
APPLICATION TEMPERATURE	45°F (7°C) to 100°F (38°C)
CURE TIME	24 hours, dry to touch
FILM THICKNESS	40 mils dry
SOLIDS	63% ± 2% [percent by weight]
DENSITY	8.6 ± 0.4 lb/gal
APPLICATION	Brush/Roll

#### 0420/EDCSDS

Please refer to our website at [www.tremcosealants.com](http://www.tremcosealants.com) for the most up-to-date Data Sheet.

#### Tremco Construction Products Group

3735 Green Rd  
Beachwood OH 44122  
800.876.5624

1451 Jacobson Ave  
Ashland OH 44805  
419.289.2050 / 800.321.6357

220 Wicksteed Ave  
Toronto ON M4H1G7  
416.421.3300 / 800.363.3213

1445 Rue de Coulomb  
Boucherville QC J4B 7L8  
514.521.9555