


Poly-Wej Gaskets

Product Description

Tremco Poly-Wej Gaskets are designed for use in compression glazing systems. They are available as a standard in EPDM. When used in combination with Tremco PoLYshim™ II Tape and gunnable sealants, the Poly-Wej Glazing System is formed. This system is proven and "clean and easy" to install, affording many years of excellent performance.

Metal Requirements

Tremco Poly-Wej Gaskets require a .062" x .062" (1.57 mm x 1.57 mm) metal nub for proper engagement. Custom Poly-Wej gaskets can be designed or may be available to accommodate specific metal nub configurations not shown.



PS-1125E for 1/8" (3.18mm) F.C. PS-1125N

PS-1126E for 3/16"(4.78mm) F.C. PS-1126N

PS-1127E for 1/4" (6.35mm) F.C. PS-1127N

*F.C.= Face Clearance

Availability

Tremco Poly-Wej Gaskets for 1/8"(3.18 mm), 3/16" (4.78 mm) and 1/4" (6.35 mm) designed face clearances are immediately available from the Tremco plant located in Ashland, Ohio. Their costs can be obtained from your local Tremco Representative or our Customer Service Department in Ashland, Ohio at: 800- 321-6357.

Poly-Wej gasket for 3/8" (9.52 mm) designed face clearance is available as a custom order with a 3 to 5 week lead time.

Packaging

Tremco Poly-Wej Gaskets are packaged based on customer requirements, profile size, configuration and the need for molded picture frame gaskets.

Warranty

Tremco warrants its Products to be free of defects in materials but makes no warranty as to appearance or color. Since methods of application and on-site conditions are beyond our control and can affect performance, Tremco makes no other warranty, expressed or implied, including warranties of MERCHANTABILITY and FITNESS FOR A PARTICULAR PURPOSE with respect to Tremco Products. Tremco's sole obligation shall be, at its option, to replace or to refund the purchase price of the quantity of Tremco Products proven to be defective, and Tremco shall not be liable for any loss or damage.

Please refer to our website at www.tremcosealants.com for the most up-to-date Product Data Sheets.

NOTE: All Tremco Safety Data Sheets (SDS) are in alignment with the Globally Harmonized System of Classification and Labelling of Chemicals (GHS) requirements.

TYPICAL PHYSICAL PROPERTIES			
PROPERTY	TEST METHOD	EPDM	NEOPRENE*
Shore "A" Hardness	ASTM D2240	68 - 71	68 - 72
Compression Set, 22 hr @ 212 °F (100 °C)	ASTM D395	24 - 28%	22 - 26%
Ozone Resistance, 100 mPa 100 hr @ 104 °F (40 °C) 20% Elongation	ASTM D1149	No Cracks	No Cracks
Tensile Strength	ASTM D412	1810 -1925 psi (12.5 – 13.3 MPa)	1850 - 2050 psi (12.8 – 14.1 MPa)
Elongation @ Rupture	ASTM D412	350 - 530%	235 - 350%
Tear Strength	ASTM D624	143 - 209 lb/in (25 – 36.6 kN/M)	163 – 190 lb/in (28.5 – 33.3 kN/M)
Brittleness Temperature @ -40°F (-40°C)	ASTM D746	Pass	Pass
Flame Propagation, Option II	ASTM C1166	No Limit	No Limit

