



# TECHNICAL DATA SHEET

**TREMproof® 201/60**  
Fluid-Applied, Elastomeric Waterproofing

---

## PRODUCT DESCRIPTION

TREMproof® 201/60 is a high-solids, VOC compliant, modified polyurethane waterproofing membrane. It is a one-part moisture-curing elastomer available in three viscosities: Self-Leveling (SL), Roller (R) and Trowel. (Trowel grade intended for detailing work only).

---

## BASIC USES

TREMproof 201/60 is designed for use on backfilled walls, split slabs that slopes to drain, primarily on concrete, masonry and plywood.

---

## FEATURES & BENEFITS

- TREMproof 201/60 is an economical choice for when construction schedules are not compressed.
- Compatible with Tremco sealants, coatings and expansion joints, which is essential for tie-ins, detailing and penetrations.

---

## AVAILABILITY

Immediately available from your local Tremco Sales Representative, Tremco distributor, or Tremco warehouse.

---

## COVERAGE RATES

Approximately 25 ft<sup>2</sup>/gal (0.61 M<sup>2</sup>/L) at 60 wet mils.

---

## PACKAGING

5-gal (19-L) pails, 36 pails/pallet

---

## LIMITATIONS

- Not for use in submerged or gas vapor conditions.
- Do not apply to damp or contaminated surfaces.
- Not to be used as an exposed or wearing surface.
- Not approved for direct contact with asphalt-based products.
- Use with adequate ventilation.
- Contact your local Tremco Sales Representative or Tremco Technical Services for compatibility information and job-specific recommendations on tie-in and termination details.

---

## WARRANTY

A repair or replacement warranty is available on all Tremco products. Visit <https://www.tremcosealants.com/warranties/> for details.

## TYPICAL PHYSICAL PROPERTIES

PROPERTY	DESCRIPTION	TEST METHOD	TYPICAL VALUES
Type	Modified Polyurethane Waterproofing		
Color	Black		
Solids	No less than 85%*		
Application	Roller/Trowel/Squeegee		
Thickness	60 mils		
Adhesion-in-Peel after Water Immersion (Unprimed)		ASTM C836; ASTM C 794	8 lbf/in (14.00 N/cm)
Weight Loss 20% maximum Loss 80% Solids minimum		ASTM C836; ASTM C 1250	9 to 12% Loss 88 to 92% Solids
Low Temperature Crack Bridging		ASTM C836; ASTM C1305	Pass
Extension after heat aging No observable cracking		ASTM C836; ASTM C1522	Pass
Hardness, Type 00 50 Min.		ASTM C836; ASTM D 2240	58 to 64
Maximum V.O.C.		Method 310	No more than 95 g/L*
Shelf Life Stability		6 months	12 months
Application Temperature		Above 40 °F (5 °C) and rising. If installing below 40 °F (5 °C), please contact Tremco Technical Service at 866-209-2404.	
Storage Temperature		40 to 100 °F (5 to 37 °C)	

\*Varies Depending on grade of material used.

\*\*Modified ASTM C1305

Please refer to our website at [www.tremcosealants.com](http://www.tremcosealants.com) for the most up-to-date Product Data Sheets.

**NOTE:** All Tremco Safety Data Sheets (SDS) are in alignment with the Globally Harmonized System of Classification and Labelling of Chemicals (GHS) requirements.

TP201-60-DS/0923



Tremco Construction Products Group (CPG) brings together the Commercial Sealants & Waterproofing and Roofing & Building Maintenance divisions of Tremco CPG Inc.; Dryvit and Willseal brands; Nudura Inc.; Prebuck LLC; Tremco Barrier Solutions, Inc.; Weatherproofing Technologies, Inc.; Weatherproofing Technologies Canada, Inc.; and Pure Air Control Services, Inc.



[tremcosealants.com](http://tremcosealants.com) | 800.321.7906



Construction Products Group

3735 Green Rd. | Beachwood, OH 44122  
800.321.7906 | [tremcocpg.com](http://tremcocpg.com)