



TECHNICAL DATA SHEET

TREMCO™ Sealer 200

A UV-Stable Aliphatic Polyurethane Sealer.

PRODUCT DESCRIPTION

TREMCO Sealer 200 is a medium-duty, two-component, ASTM Type V, aliphatic polyurethane coating applied over urethane cement systems. The aliphatic urethane chemistry offers excellent color stability and resistance to UV degradation. Impact and stain resistance are inherent qualities of TREMCO Sealer 200.

BASIC USES

TREMCO Sealer 200 is a protective aliphatic polyurethane coating that can be applied over TREMfloor™ Urethane Cement Systems.

Recommended Applications:

- Warehouses and Manufacturing Areas
- Airplane Hangars (Jet Fuel)
- Maintenance Areas
- Food and Beverage Areas

FEATURES & BENEFITS

- High Solids
- Excellent Color Stability
- Good Stain Resistance
- Chemical Resistance
- UV Degradation Resistance
- Cleanability: Withstands high temperature daily cleaning protocols
- Easy application and fast setting for minimal downtime.

COVERAGE RATE

250-300 sq ft per gal @ 6 mils WFT

MIX RATIO

TREMCO Sealer 200 Kit Mix Ratio: (2:1)

PACKAGING

TREMCO Sealer 200 is available in 1 gal units. All components come packaged together in a case which includes the following pre-measured components: (*Do not split or break components*)

- TREMCO Sealer 200 Part A (0.65 gal)
- TREMCO Sealer 200 Part B (0.35 gal)

AVAILABILITY

Immediately available from a Tremco Sales Representative.

COLORS

TREMCO Sealer 200 is available in Clear gloss.

LIMITATIONS

- Do not apply to damp or contaminated surfaces.
- Proper ventilation is required.
- Keep open flames and sparks away from the area where materials are being mixed and applied.

WARRANTY

A repair or replacement warranty is available on all Tremco products. Visit <https://www.tremcosealants.com/warranties/> for details.

PHYSICAL PROPERTIES		
PROPERTY	TEST METHOD	TYPICAL RESULTS
VOC	ASTM D2369	<5 grams/liter
Solids by Volume	Calculation	78%
Pencil Hardness	ASTM D3363	2H
Taber Abrasion, CS-17 Wheel Impact	ASTM D-4060	25mg
-Direct Impact	ASTM D-4060	> 160-inch lbs
-Indirect Impact	ASTM D-4060	>160-inch lbs
Drying Time, 6 mils WFT	ASTM D1640	6 hours
Gloss 60°	D523	85-90
Pot Life		
- 50°F (10°C)		90 min
- 75°F (24°C)		60 min
- 90°F (32°C)		45 min
Cure Time (Temperature Dependent)		
- Foot Traffic		*≈8-12 hours
- Full Service		*≈24 hours
- Chemical Resistance		*≈3-4 days

Please refer to our website at www.tremcosealants.com for the most up-to-date Product Data Sheets.

NOTE: All Tremco Safety Data Sheets (SDS) are in alignment with the Globally Harmonized System of Classification and Labelling of Chemicals (GHS) requirements.

SEALR200DS/1022

Tremco Construction Products Group (CPG) brings together the Commercial Sealants & Waterproofing and Roofing & Building Maintenance divisions of Tremco CPG Inc.; Dryvit, Nudura and Willseal brands; Prebuck LLC; Tremco Barrier Solutions, Inc.; Weatherproofing Technologies, Inc.; Weatherproofing Technologies Canada, Inc.; and Pure Air Control Services, Inc.



tremcosealants.com | 800.321.7906



Construction Products Group

3735 Green Rd. | Beachwood, OH 44122
800.321.7906 | tremcocpg.com