



# TECHNICAL DATA SHEET

## TREMproof® TRA SHEETING

Reinforced Flashing Membrane  
Embedded in TREMproof 250GC

---

### PRODUCT DESCRIPTION

TREMproof® TRA Sheeting is a protective waterproofing course that is compounded from a blend of EPDM and SBR thermostat elastomers. This sheet is reinforced with a high-strength, polyester-woven scrim.

---

### BASIC USES

TREMproof TRA Elastomeric Sheeting is designed to provide a durable, flexible, tear-resistant bridge in areas of high movement where cold- and hot-applied membranes are being utilized. TRA Elastomeric Sheeting can also be used as a secondary layer of waterproofing for the TREMproof 250GC Cold-Applied, Heavy-Duty Waterproofing System.

---

### FEATURES & BENEFITS

- EPDM/SBR blend provides flexibility for ease of installation.
- Woven polyester scrim for added durability and puncture resistance.
- TRA Sheeting has the versatility to be utilized in TREMproof 250GC applications.
- TRA Sheeting provides an additional waterproofing layer for ultimate protection.
- Superior tensile and tear strength for high stress, heavy-duty applications.

---

### AVAILABILITY

Immediately available from your local Tremco Sales Representative or Tremco Distributor. For distributor locations, visit [www.tremcosealants.com](http://www.tremcosealants.com).

---

### PACKAGING

20" (508 mm), 30"(762 mm) x 50' (15.24 M) rolls  
60" (1,524 mm) x 100' (30.48 M) rolls

---

### STORAGE

TREMproof TRA Sheeting should be stored out of direct sunlight. Vertical storage is recommended.

---

### LIMITATIONS

- Not for use beneath sand-set vehicular pavers.

---

### WARRANTY

A repair or replacement warranty is available on all Tremco products. Visit <https://www.tremcosealants.com/warranties/> for details.

## TYPICAL PHYSICAL PROPERTIES

PROPERTY	TEST METHOD	TYPICAL VALUES
Color		Black
Thickness	ASTM D751-89	0.045" (1.1 mm)
Weight	ASTM D751-89	41.6 oz/yd <sup>2</sup> (1,422 g/M <sup>2</sup> )
Breaking Strength	ASTM D751-89	261 lbf (1,443 N) MD 150 lbf (1,288 N) XMD
Tear Strength	ASTM D751-89	94 lbf (313 N) MD 59 lbf (348 N) XMD
Low Temperature Flexibility (-40 °F)	ASTM D2136-84	Pass

Please refer to our website at [www.tremcosealants.com](http://www.tremcosealants.com) for the most up-to-date Product Data Sheets.

NOTE: All Tremco Safety Data Sheets (SDS) are in alignment with the Globally Harmonized System of Classification and Labelling of Chemicals (GHS) requirements.

TRADS/1023

Tremco Construction Products Group (CPG) brings together Tremco CPG Inc. and its Dryvit and Nudura brands; Willseal; Prebuck LLC; Tremco Barrier Solutions, Inc.; Weatherproofing Technologies, Inc. and its Pure Air Control Services and Canam Building Envelope Specialists offerings; and Weatherproofing Technologies Canada, Inc.



[tremcosealants.com](http://tremcosealants.com) | 800.321.7906



Construction Products Group

3735 Green Rd. | Beachwood, OH 44122  
800.321.7906 | [tremcocpg.com](http://tremcocpg.com)