

**Product Description**

TREMstop® Smoke & Sound Spray is an acrylic latex sealant for use in smoke rated partitions or joints and to prevent sound transmission through unprotected openings.

**Basic Uses**

TREMstop Smoke & Sound Spray may be used for both through-penetrations and joints in smoke or sound rated partitions.

**Features and Benefits**

- TREMstop Smoke & Sound Spray is designed to meet the needs of both smoke and sound rated partitions with one product. It can be painted once dry and is easily cleaned up with soapy water. The spray application affords labor savings, especially on long joint runs.

**Availability**

Immediately available from your local Tremco Field Representative, Tremco Distributor or Tremco Warehouse.

**Coverage Rates**

12.83 ft<sup>2</sup>/gal

**Packaging**

5-gal (19-L) pails

**Colors**

White

**Shelf Life**

Minimum 1 year when stored at 40 to 110 °F (5 to 43 °C)

**Limitations**

- Not for use in fire-rated assemblies.

**Clean Up**

Excess sealant can be cleaned up or removed with soapy water before sealant skins. Clean sprayer in accordance with manufacturer's recommended cleaning instructions.

**Warranty**

Tremco warrants its Products to be free of defects in materials, but makes no warranty as to appearance or color. Since methods of application and on-site conditions are beyond our control and can affect performance, Tremco makes no other warranty, expressed or implied including warranties of MERCHANTABILITY and FITNESS FOR A PARTICULAR PURPOSE, with respect to Tremco Products. Tremco's sole obligation shall be, at its option, to replace, or refund the purchase price of the quantity of Tremco Products proven to be defective and Tremco shall not be liable for any loss or damage.

Please refer to our website at [www.tremcosealants.com](http://www.tremcosealants.com) for the most up-to-date Product Data Sheets.

NOTE: All Tremco Safety Data Sheets (SDS) are in alignment with the Globally Harmonized System of Classification and Labelling of Chemicals (GHS) requirements.

**TYPICAL PHYSICAL PROPERTIES**

PROPERTY	TEST METHOD	TYPICAL VALUES
V.O.C. Content		35 g/L
Movement Capability	ASTM C719	+/- 25%
STC	ASTM E90	Restored to 59 in a U411 wall
Peel Strength	ASTM C794	8 to 14 (substrate dependent)
pH		7 to 9
Antifungal		Contains antifungal additive

