

Product Description

TremPRO® RV Roof Sealant is a high performance, low modulus, one-component, self-leveling sealant designed for RV roof penetrations as a primary seal. The sealant cures to a flexible rubber when exposed to atmospheric moisture.

Basic Uses

TremPRO® RV Roof Sealant is specially designed for sealing level or slightly sloped joints, seams and penetrations in recreational vehicle and trailer roofs.

Features and Benefits

- TremPRO® RV Roof Sealant cures to withstand movement, shear, deflection and moisture in lap and butt joint applications.
- TremPRO® RV Roof Sealant exhibits excellent adhesion to steel, painted metal, wood, vinyl, concrete and composite surfaces.
- The product can be painted shortly after it has developed a robust skin.

Packaging

11 oz. (300 ml)

Colors

White

Availability

Immediately available from your local Tremco Field Representative, Tremco Distributor or Tremco Warehouse.

Limitations

- Do not apply over damp or contaminated surfaces.

Substrate Preparation

For best adhesion, the surface must be sound, clean and dry. Depending on the substrate, the surface may require mechanical cleaning such as a thorough wire brushing with steel wool or Scotch Brite pad and/ or solvent wipe. Old sealant must also be removed prior to application.

Application

TremPRO® RV Roof Sealant is easy to apply with conventional caulking equipment. Fill seam completely and tool. Ensure 1" overlap. At 75 °F (23.9 °C), 50% RH, a durable skin forms within hours after application.

Damaged Sealant can be repaired. Consult Tremco Technical Service or your Tremco sales representative for repair procedures.

Clean Up

Tooling is recommended immediately after application to ensure firm, intimate contact with the joint interface. Dry tooling is preferred. Excess sealant and smears adjacent to the joint can be removed with Xylol or Toluol before sealant cures.

Warranty

Tremco warrants its Products to be free of defects in materials but makes no warranty as to appearance or color. Since methods of application and on-site conditions are beyond our control and can affect performance, Tremco makes no other warranty, expressed or implied including warranties of MERCHANTABILITY and FITNESS FOR A PARTICULAR PURPOSE, with respect to Tremco Products. Tremco's sole obligation shall be, at its option, to replace, or refund the purchase price of the quantity of Tremco Products proven to be defective and Tremco shall not be liable for any loss or damage.

TYPICAL PHYSICAL PROPERTIES

PROPERTY	TEST METHOD	TYPICAL VALUES
Effects of Accelerated Weathering		Passes
Extrusion Rate		10 to 15 sec
Rheological Properties		Levels Moderately; Holds up to 5 to 6% slope
Skin Formation		45 to 60 min (typical)
Tack Free Time		1 to 2 hr
Adhesion to EPDM	180° Peel Adhesion Test	7.64 dry lbf
Adhesion to Galvanized Metal	180° Peel Adhesion Test	10.58 dry lbf
Adhesion to PVC	180° Peel Adhesion Test	10.13 dry lbf
Adhesion to TPO	180° Peel Adhesion Test	.61 dry lbf
Adhesion to TremPRO RV Premium Roof Coating	180° Peel Adhesion Test	4.92 dry lbf
Adhesion to Vinyl	180° Peel Adhesion Test	6.97 dry lbf

Please refer to our website at www.tremcosealants.com for the most up-to-date Product Data Sheets.

NOTE: All Tremco Safety Data Sheets (SDS) are in alignment with the Globally Harmonized System of Classification and Labelling of Chemicals (GHS) requirements.

1018/TPRORVRSDS-ST



Tremco Commercial Sealants & Waterproofing

3735 Green Rd
Beachwood OH 44122
216.292.5000 / 800.321.7906

1451 Jacobson Ave
Ashland OH 44805
419.289.2050 / 800.321.6357

220 Wicksteed Ave
Toronto ON M4H1G7
416.421.3300 / 800.363.3213

1445 Rue de Coulomb
Boucherville QC J4B 7L8
514.521.9555