

### Product Description

Tremco® EPDM Rubber Extrusions are extruded and fabricated into gaskets and accessories for use in sealing and glazing industrial and transportation OEM applications. Tremco rubber extrusions are available in a peroxide formulation for applications in which cure-enhanced memory and rebound characteristics are necessary.

### Basic Uses

TremPro EPDM Rubber Extrusions are used in a variety of OEM applications. These include vehicle glazing systems, bumpers, glazing gaskets, air seals, decorative trim and caps, O-rings and specialty extrusions. TremPro EPDM Rubber Extrusions can also be butt-spliced, cut to length or molded into corners. There are also Pressure Sensitive Adhesives available for applications where improved bond performance is required or the elimination of mechanical fasteners is desired.

### Availability

TremPro EPDM Rubber Extrusions are generally custom manufactured but many standard designs are available. Availability and cost may be obtained from your local Tremco industrial representative, or by contacting our Customer Service Department in Ashland, Ohio, at 800-321-6357 or in Canada at 800-323-3213.

### Packaging

TremPro EPDM Dense Rubber Extrusions are packaged based on customer requirements, profile size, configuration and other needs as specified by the customer.

### Warranty

Tremco warrants its Products to be free of defects in materials, but makes no warranty as to appearance or color. Since methods of application and on-site conditions are beyond our control and can affect performance, Tremco makes no other warranty, expressed or implied including warranties of MERCHANTABILITY and FITNESS FOR A PARTICULAR PURPOSE with respect to Tremco Products. Tremco's sole obligation shall be, at its option, to replace or refund the purchase price of the quantity of Tremco Products proven to be defective, and Tremco shall not be liable for any loss or damage.

Please refer to our website at [www.tremcosealants.com](http://www.tremcosealants.com) for the most up-to-date Product Data Sheets.

NOTE: All Tremco Safety Data Sheets (SDS) are in alignment with the Globally Harmonized System of Classification and Labelling of Chemicals (GHS) requirements.

## TYPICAL PHYSICAL PROPERTIES

PROPERTY	TEST METHOD	60 DUROMETER	70 DUROMETER	80 DUROMETER
Shore "A" Hardness	ASTM D2240	58 to 62	68 to 71	82 to 85
Compression Set, 22 hr @ 212 °F (100 °C), Ozone Resistance, 100 mPa	ASTM D395	18 to 29%	22 to 28%	26 to 30%
Ozone Resistance, 100 mPa 100 hr @ 104 °F (40 °C) 20% Elongation	ASTM D1149	No Cracks	No Cracks	No Cracks
Tensile Strength	ASTM D412	1675 to 1750 psi (11.5 to 12.1 MPa)	1810 to 1925 psi (12.5 to 13.3 MPa)	1700 to 1900 psi (11.7 to 13.1 MPa)
Elongation @ Rupture	ASTM D412	375 to 550%	350 to 530%	175 to 280%
Tear Strength	ASTM D624	160 to 182 lb/in (28.0 to 31.9 kN/M)	143 to 209 lb/in (25.0 to 36.6 kN/M)	125 to 158 lb/in (21.9 to 27.7 kN/M)
Brittleness Temperature @ -40°F (-40°C)	ASTM D746	Pass	Pass	Pass
Flame Propagation, Option II	ASTM C1166	No Limit	No Limit	No Limit

0316/TPROEPDMDS-GL



### Tremco Commercial Sealants & Waterproofing

3735 Green Rd  
Beachwood OH 44122  
216.292.5000 / 800.321.7906

1451 Jacobson Ave  
Ashland OH 44805  
419.289.2050 / 800.321.6357

220 Wicksteed Ave  
Toronto ON M4H1G7  
416.421.3300 / 800.363.3213

1445 Rue de Coulomb  
Boucherville QC J4B 7L8  
514.521.9555