

Product Description

Tremco DualFlex® is a reinforcing flashing that consists of a central strip of elastomeric SEBS rubber flanked on either side by an absorbent non-woven felt. The felt allows for easy integration of the flashing and the waterproofing membrane. The elastomeric SEBS rubber provides superior movement capability without compromising the waterproofing.

Basic Uses

Tremco DualFlex is used as a flashing material at joints, transitions in plane, horizontal-to-vertical transitions and any other situation in waterproofing where durable, reinforcing sheeting is desired. Tremco DualFlex is ideal for use with TREMproof® hot-applied waterproofing membranes and Vulkem® deck coating basecoats, Vulkem® EWS coating systems and TREMproof PUMA below grade waterproofing systems.

Availability

Immediately available from your local Tremco Sales Representative or Tremco Distributor. For Distributor locations visit www.tremcosealants.com.

Packaging

9.5" x 98' (240 mm x 30 M) rolls

6" x 98' (150 mm x 30 M) rolls

19" x 98' (480 mm x 30 M) rolls

Fire Rated Systems

None presently listed. For firestop engineering judgement requests please visit www.tremcosealants.com or contact Tremco Technical Services at 866-209-2404.

Limitations

- Not for use with Tremco TREMproof® 201/60 or TREMproof 250GC cold fluid-applied waterproofing membranes.

Warranty

Tremco warrants its Products to be free of defects in materials, but makes no warranty as to appearance or color. Since methods of application and on-site conditions are beyond our control and can affect performance, Tremco makes no other warranty, expressed or implied, including warranties of MERCHANTABILITY and FITNESS FOR A PARTICULAR PURPOSE, with respect to Tremco Products. Tremco's sole obligation shall be, at its option, to replace or to refund the purchase price of the quantity of Tremco Product proven to be defective, and Tremco shall not be liable for any loss or damage.

Please refer to our website at www.tremcosealants.com for the most up-to-date Product Data Sheets.

NOTE: All Tremco Safety Data Sheets (SDS) are in alignment with the Globally Harmonized System of Classification and Labelling of Chemicals (GHS) requirements.

TYPICAL PHYSICAL PROPERTIES

PROPERTY	TEST METHOD	US VALUES	SI VALUES
Color		Gray	
Resistance to Temperature min/max		-22 °F to 194 °F	-30°C to 90°C
Thickness		0.055 in	1.4 mm
Breaking Load Longitudinal	DIN EN ISO 527-3		251N / 15mm
Breaking Load Lateral	DIN EN ISO 527-3		42 N / 15mm
Extension Break Longitudinal	DIN EN ISO 527-3		32%
Extension Break Lateral	DIN EN ISO 527-3		122%
Resistance to Water Pressure	DIN EN 1928 (Version B)	>21.7 psi	>1.5 psi
UV Resistance min	DIN EN ISO 4892-2		500 h



0920/DUALFLEXDS-BG

Tremco Commercial Sealants & Waterproofing

3735 Green Rd
Beachwood OH 44122
216.292.5000 / 800.321.7906

1451 Jacobson Ave
Ashland OH 44805
419.289.2050 / 800.321.6357

220 Wicksteed Ave
Toronto ON M4H1G7
416.421.3300 / 800.363.3213

1445 Rue de Coulomb
Boucherville QC J4B 7L8
514.521.9555