

Product Description

Tremco PUMA Primer is a methyl-methacrylate (MMA), two-component primer for porous and non-porous substrates. Tremco PUMA Primer must be used with Initiator.

Basic Uses

Tremco PUMA Primer is used on concrete, metal and wood surfaces before a Tremco PUMA base coat is applied.

Features and Benefits

- Rapid cure times allows for base coat application within 30 min.
- Acceptable for use at temperatures below 20 °F, allowing for continuation of projects in the colder months.
- Initiator adjustments allow for 30 to 45 min cure time between applications independent of temperature.
- Compatible with most Tremco sealants and coatings allowing for seamless transitions and warrantable connectivity between systems and detail work.
- Unique chemistry allows for easy repair and the ability to apply additional coats for extended periods even after initial cure.

Availability

Immediately available from your local Tremco Sales Representative.

Packaging

Tremco PUMA Primer: 6-gal pails

Installation

Concrete shall be water-cured and attain a 3000 PSI minimum compressive strength for waterproofing applications, 4000 PSI for vehicular traffic. Concrete finish shall be a light steel trowel followed by an equivalent ICRI #3-#4 finish. Moisture content in the concrete must be less than 6% as measured using a Tramex CME 4 Moisture Meter. Depending on concrete construction and job site location, additional concrete testing may be required. Please contact your local Tremco representative.

Tremco PUMA components are designed for use with the Vulkem EWS and TREMproof PUMA systems. Please refer to the appropriate application instructions for complete application details. The techniques involved may require modification due to job-site specific conditions. Consult your Tremco representative for recommended site conditions and requirements.

Limitations

- Do not apply to damp or contaminated surfaces.
- Use with adequate ventilation.

Warranty

Tremco warrants its Products to be free of defects in materials but makes no warranty as to appearance or color. Since methods of application and on-site conditions are beyond our control and can affect performance, Tremco makes no other warranty, expressed or implied, including warranties of MERCHANTABILITY and FITNESS FOR A PARTICULAR PURPOSE with respect to Tremco Products. Tremco's sole obligation shall be, at its option, to replace or to refund the purchase price of the quantity of Tremco Products proven to be defective, and Tremco shall not be liable for any loss or damage.

Please refer to our website at www.tremcosealants.com for the most up-to-date Product Data Sheets.

NOTE: All Tremco Safety Data Sheets (SDS) are in alignment with the Globally Harmonized System of Classification and Labelling of Chemicals (GHS) requirements.

TYPICAL PHYSICAL PROPERTIES

PROPERTY	TEST METHOD	TREMCO PUMA PRIMER
% Solids (by Weight)	ASTM D1353	100%
Drying Time @ 75°F, 50% RH	ASTM D1640	17 mil film, 1 hr
Weathering	ASTM D822 Weatherometer 350 hr	N/A
Cure Time		30 min

0118/PUMAPRIMERDS

Please refer to our website at www.tremcosealants.com for the most up-to-date Product Data Sheets.

Tremco Commercial Sealants & Waterproofing

3735 Green Rd
Beachwood OH 44122
216.292.5000 / 800.321.7906

1451 Jacobson Ave
Ashland OH 44805
419.289.2050 / 800.321.6357

220 Wicksteed Ave
Toronto ON M4H1G7
416.421.3300 / 800.363.3213

1445 Rue de Coulomb
Boucherville QC J4B 7L8
514.521.9555