

Product Description

A spun-bonded polyester fabric style 2011, consisting of a nonwoven fabric of continuous filament polyester fibers that are randomly arranged. These fibers are highly dispersed and bonded at the filament junctions.

Basic Uses

Tremco® Reinforcing Fabric is used to reinforce hot fluid-applied membranes in multi-lift applications.

Availability

Immediately available from your local Tremco Sales Representative or Tremco Distributor. For Distributor locations visit www.tremcosealants.com.

Packaging

- 84 in. x 675 ft. (2.13m x 205.74 m) roll
- 36 in. x 600 ft. (0.91m x 183m) roll
- 12 in. x 600 ft. (30cm x 183m) roll

Warranty

Tremco warrants its Products to be free of defects in materials, but makes no warranty as to appearance or color. Since methods of application and on-site conditions are beyond our control and can affect performance, Tremco makes no other warranty, expressed or implied, including warranties of MERCHANTABILITY and FITNESS FOR A PARTICULAR PURPOSE, with respect to Tremco Products. Tremco's sole obligation shall be, at its option, to replace or to refund the purchase price of the quantity of Tremco Product proven to be defective, and Tremco shall not be liable for any loss or damage.

Please refer to our website at www.tremcosealants.com for the most up-to-date Product Data Sheets.

NOTE: All Tremco Safety Data Sheets (SDS) are in alignment with the Globally Harmonized System of Classification and Labelling of Chemicals (GHS) requirements.

TYPICAL PHYSICAL PROPERTIES

PROPERTY	TEST METHOD	TYPICAL VALUES
Color		White
Weight	ASTM D3776	0.75 oz/y ² (25 gsm)
Thickness (Mil)	ASTM D1777	8.0 mil (0.20 mm)
Sheet Grab Tensile (lb - MD x XD)	ASTM D4632	15.4 lbs x 11.2 lbs (69 x 50 N)
Trapezoid Tear (lb - MD x XD)	ASTM D1117	4.9 lbs x 5.8 lbs (21.8 x 25.8 N)



0718/REEMAYDS-BG

Tremco Commercial Sealants & Waterproofing

3735 Green Rd
Beachwood OH 44122
216.292.5000 / 800.321.7906

1451 Jacobson Ave
Ashland OH 44805
419.289.2050 / 800.321.6357

220 Wicksteed Ave
Toronto ON M4H1G7
416.421.3300 / 800.363.3213

1445 Rue de Coulomb
Boucherville QC J4B 7L8
514.521.9555