



TECHNICAL DATA SHEET

TREMSIL® 200
Single-Component, Acetoxy
Silicone Sealant

PRODUCT DESCRIPTION

Tremsil® 200 is a single component, acetoxy silicone sealant. Tremsil 200 cures to a flexible rubber when exposed to moisture present in the air.

BASIC USES

Tremsil 200 produces a weathertight seal to glass, metal, porcelain, ceramic, and most painted surfaces. Tremsil 200 sealant is suitable for use in kitchens, bathrooms, spas, and similar applications.

FEATURES & BENEFITS

Tremsil 200 is easy to apply with conventional caulking equipment. Tremsil 200 may be used in any joint designed in accordance with accepted architectural/engineering practices. Joint width should be 4 times anticipated movement, but not less than 1/4" (6 mm) wide.

Applicable Standards:

- Conforms to ASTM C 920 Type S, Grade NS, use NT, G, A, and O
- U.S. Federal Specification TT-S-00230, Class A
- U.S. Federal Specification TT-S-001543A, Class A
- CAN/CGSB-19.13-M87

Tremsil 200's Greenguard Gold certification ensures safety for use in the most sensitive indoor environments including hospitals and schools.

AVAILABILITY

10.1 oz (300 mL) cartridges are immediately available from your local Tremco Field Representative, Tremco Distributor, or Tremco Warehouse.

COLORS

Aluminum, Black, Clear, Dark Bronze, Gray, and White.

LIMITATIONS

Do not apply over damp or contaminated surfaces. Not intended for continuous water immersion. Do not use on surfaces sensitive to corrosion by acetic acid vapors (a by-product of sealant cure). Use with adequate ventilation.

WARRANTY

Tremco warrants its Products to be free of defects in materials but makes no warranty as to appearance or color. Since methods of application and on-site conditions are beyond our control and can affect performance, Tremco makes no other warranty, expressed or implied including warranties of MERCHANTABILITY and FITNESS FOR A PARTICULAR PURPOSE with respect to Tremco Products. Tremco's sole obligation shall be, at its option, to replace or refund the purchase price of the quantity of Tremco Products proven to be defective, and Tremco shall not be liable for any loss or damage.

TYPICAL PHYSICAL PROPERTIES

PROPERTY	TEST METHOD	TYPICAL RESULTS
As Supplied:		
Skin Forming Time		20 min
Density	ISO 1183-1 A	1.01 g/cm ³
Consistency	ISO 7390, Profile U 20	Non-Sag
Extrusion Rate – Mass Flow		500 g/min
Application Temperature Range		5 to 40°C (41 to 104°F)

As Cured:		
Movement Capability	ISO 11600	25%
Modulus at 100% Elongation	ISO 8339-A	0.38 N/mm ²
Elongation at Break	ISO 8339	250%
Hardness Shore A	ISO 868	18
Tear Strength	ISO 34, Method C	4.5 N/mm
Tensile Strength	ISO 8339	0.70 N/mm ²
Service Temperature Range		-40 to 100°C (-40 to 212°F)



Tremco Commercial Sealants & Waterproofing | tremcosealants.com

0422/T200DS-ST

3735 Green Rd
Beachwood OH 44122
216.292.5000 / 800.321.7906

1451 Jacobson Ave
Ashland OH 44805
419.289.2050 / 800.321.6357

220 Wicksteed Ave
Toronto ON M4H1G7
416.421.3300 / 800.363.3213

1350 Gay-Lussac, Unit: 3
Boucherville QC J4B 7G4
514.521.9555

