



WATCHDOG WATERPROOFING®

Spray applied, polymer-enhanced, asphalt membrane

DATA SHEET

Installation

Surface preparation

The wall surface should be smooth and monolithic. Remove loose aggregate and sharp protrusions from the wall. Voids, spalled areas and exposed aggregate should be patched with suitable mastic or non-shrinking grout before spraying. WATCHDOG WATERPROOFING does not require any priming or special preparation.

Membrane application

The WATCHDOG membrane is sprayed evenly over the entire foundation wall. The membrane can be applied when ambient temperatures are as low as -18°C (0°F), allowing for fewer construction delays. However, the membrane must not be applied over standing water, a water or ice film, frost, ice or snow. On poured concrete basements, WATCHDOG can be applied as soon as the forms are removed, and on parged block basements as soon as the mortar is dry.

Curing and backfilling

Foundations coated with WATCHDOG WATERPROOFING should be allowed to cure at least 16 to 24 hours before backfilling. Backfilling should comply with local code requirements.

Drainage requirements

WATCHDOG WATERPROOFING is designed for use with a foundation drainage system consistent with local codes and good construction practices. A typical exterior drainage system consists of 75-100mm (3 or 4-inch) minimum perforated drainage pipe, with gravel over the pipe, on the footer and up the face of the vertical wall, or as specified by local code. The drain tile should channel water to either an operating sump pump or to daylight. The grade should always slope away from the foundation.

Environmentally Responsible

The WATCHDOG membrane uses a non-flammable, water-based carrier that is environmentally responsible. It has been thoroughly tested by independent labs to prove that no harmful leaching of the membrane occurs.

Availability

WATCHDOG WATERPROOFING is available through your local Tremco Select Contractor.

Please refer to our website at www.tremcosealants.com for the most up-to-date Product Data Sheets.

NOTE: All Tremco Safety Data Sheets (SDS) are in alignment with the Globally Harmonized System of Classification and Labelling of Chemicals (GHS) requirements.

TYPICAL PHYSICAL PROPERTIES

PROPERTY	DESCRIPTION	
TYPE	Polymer-enhanced asphalt liquid-applied membrane	
COLOR	Black	
SOLIDS	64% ± 3% [percent by weight]	
DENSITY	8.2 ± .15 lbs/gal	
APPLICATION	Airless spray	
APPLICATION TEMPERATURE	Minimum -18°C (0°F)	
APPLICATION THICKNESS	60 mils (wet) ¹	
TYPICAL CURE TIME	16-24 hrs ²	
PROPERTY	TEST METHOD	TYPICAL RESULTS
ADHESION TO CONCRETE (PEEL, N/m)	ASTM C-836	1200 N/m
ELONGATION	ASTM D-412	>1800%
LOW TEMPERATURE FLEXIBILITY	CGSB 37.58-M86	Flexible to -20°C (-4°F)
CRACK BRIDGING ABILITY	CGSB 37.58-M86	Exceed 30 cycles at -20°C (-4°F)
WATER VAPOUR PERMEANCE	ASTM E-96 Wet Method	$< \frac{43 \text{ ng}}{\text{Pa} \cdot \text{s} \cdot \text{m}^2}$
RESISTANCE TO DEGRADATION IN SOIL	ASTM E-154	Good ³
MOLD GROWTH AND BACTERIAL ATTACK	ASTM D-3273, ASTM D-3274	No Degradation

¹ Measured in-place with an ASTM D-4414 notch film gauge, wetting the 60-mil tab. Membrane cures to [dries] to 40 mils.

² Typical cure time at 10° and 50% relative humidity (RH), may be longer for lower temperature and/or higher RH.

³ Tensile strength increased by more than 25%; minimum of 10% decrease is standard.

0220/WDWDS

Please refer to our website at www.tremcosealants.com for the most up-to-date Data Sheet.

Tremco Construction Products Group

3735 Green Rd
Beachwood OH 44122
800.876.5624

1451 Jacobson Ave
Ashland OH 44805
419.289.2050 / 800.321.6357

220 Wicksteed Ave
Toronto ON M4H1G7
416.421.3300 / 800.363.3213

1445 Rue de Coulomb
Boucherville QC J4B 7L8
514.521.9555