

EXOAIR® AIR BARRIER MEMBRANES

Self-Adhered Air & Vapor Membrane Comparison



| MEMBRANE | EXOAIR® 110 | EXOAIR® 110AT |
|--------------------------|---|---------------------------------------|
| Adhesive | SBS Rubberized Asphalt | Butyl |
| Facer Composition | HDPE (High Density Polyethylene) | HDPP (High Density Polypropolyne) |
| Facer Color | White with large green logo | White with small green logo & website |
| Mil Thickness | 40 mils | 18 mils |
| Puncture Resistance | 49 lbf | 52 lbf |
| Installation Temperature | 40°F (4°C) and rising | 20°F (-7°C) and rising |
| In-Service Temperature | Up to 158°F (70°C) | Up to 240°F (116°C) |
| Weight | 68 lbs | 39 lbs |
| Primer Required | Yes, ExoAir Primer | No |
| UV Exposure | 30 days | 12 months |
| NFPA 285 Tested Assembly | No, options with stone wool, please contact Technical Service | Yes, FWFO.EWS0010 & FWFO.EWS0019 |
| Sealants adhere to facer | Dymonic® 100 & Spectrem® 1 | Dymonic 100 & Spectrem 1 |

Tremco | 3735 Green Road | Beachwood, OH 44122 | US: 800.852.9068 | CAN: 800.363.3213 | tremcosealants.com

Tremco Construction Products Group (CPG) brings together Tremco CPG Inc. and its Dryvit and Nudura brands; Willseal; Prebuck LLC; Tremco Barrier Solutions, Inc.; Weatherproofing Technologies, Inc. and its Pure Air Control Services and Canam Building Envelope Specialists offerings; and Weatherproofing Technologies Canada, Inc.



Tremco®, ExoAir®, Dymonic® and Spectrem® are registered trademarks of Tremco Incorporated. Use of the ® symbol indicates registration with the US Patent & Trademark Office and the Canadian Intellectual Property Office.

0324/EA110&110ATCS

tremcocpg.com