

NOTES

ALL WET MIL THICKNESS MEASUREMENTS BELOW SHALL BE MEASURED USING A NOTCHED THICKNESS GAGE PER ASTM D4414.

NOTE 1: EITHER PEEL AND STICK FLASHING OR 3 LAYERS CONSISTING OF ENVIRO-DRI® MEMBRANE/JOINT FABRIC/ENVIRODRI MEMBRANE. THE FIRST LAYER SHALL BE ENVIRO-DRI MEMBRANE IN A CONTINUOUS FILM OF 13-16 WET MILS ON THE SHEATHING/SUBSTRATE MATERIAL AND 2 LAYERS CONSISTING OF JOINT FABRIC EMBEDDED INTO THE FIRST ENVIRO-DRI LAYER FOLLOWED BY 20 WET MILS OF ENVIRO-DRI MEMBRANE OVER AND SOAKED THROUGH THE FABRIC, LEAVING A SMOOTH, CONTINUOUS FILM THAT ALL BUT OBSCURES THE FABRIC TEXTURE.

NOTE 2: EITHER PEEL AND STICK FLASHING OR 5 LAYERS CONSISTING OF ENVIRO-DRI MEMBRANE/JOINT FABRIC/ENVIRO-DRI MEMBRANE/JOINT FABRIC/ENVIRO-DRI MEMBRANE. THE FIRST LAYER SHALL BE ENVIRO-DRI MEMBRANE IN A CONTINUOUS FILM OF 13-16 WET MILS ON THE SHEATHING/SUBSTRATE MATERIAL PLUS 4 LAYERS CONSISTING OF THE FOLLOWING. JOINT FABRIC EMBEDDED INTO THE FIRST ENVIRO-DRI LAYER FOLLOWED BY 20 WET MILS OF ENVIRO-DRI MEMBRANE OVER AND SOAKED THROUGH THE FABRIC FOLLOWED BY A SECOND LAYER OF JOINT FABRIC EMBEDDED INTO THE MEMBRANE OVER THE FIRST LAYER OF FABRIC AND COATED OVER AND SOAKED THROUGH WITH ANOTHER 20 WET MILS OF ENVIRO-DRI MEMBRANE LEAVING A SMOOTH, CONTINUOUS FILM THAT ALL BUT OBSCURES THE FABRIC TEXTURE.

NOTE 3: FOR ACCESSORIES WITH FLANGES (ELECTRICAL BOXES, VENTS, PENETRATION TREATMENTS, ETC.) THE FLANGES SHALL BE INSTALLED OVER ENVIRO-DRI MEMBRANE INSTALLED AT ITS STANDARD FIELD APPLICATION THICKNESS, 13-16 WET MILS. FLANGED ACCESSORIES SHALL EITHER BE FLASHED WITH PEEL AND STICK FLASHING OR 3 LAYERS CONSISTING OF ENVIRO-DRI MEMBRANE/JOINT FABRIC/ENVIRO-DRI MEMBRANE. THE FIRST LAYER SHALL BE ENVIRO-DRI MEMBRANE CONSISTING OF JOINT FABRIC EMBEDDED INTO THE FIRST ENVIRO-DRI LAYER FOLLOWED BY 20 WET MILS OF ENVIRO-DRI MEMBRANE OVER AND SOAKED THROUGH THE FABRIC, LEAVING A SMOOTH, CONTINUOUS FILM THAT ALL BUT OBSCURES THE FABRIC TEXTURE.

NOTE 4: ENVIRO-DRI COUNTER FLASHING FABRIC SHALL BE INSTALLED BY EMBEDDING A MINIMUM OF 1 INCHES OF ENVIRO-DRI COUNTER FLASHING INTO 20 WET MILS OF ENVIRO-DRI MEMBRANE. THEN THE TOP EDGE OF THE COUNTER FLASHING SHALL BE SEALED AS PER NOTE 5 BELOW USING JOINT FABRIC EMBEDDED INTO ENVIRO-DRI MEMBRANE INSTALLED A MINIMUM OF 1 INCH DOWN FROM THE TOP OF THE COUNTER FLASHING AND EXTENDING A MINIMUM OF ½ INCH BEYOND THE CORNERS OF THE COUNTER FLASHING.

NOTE 5: ENVIRO-DRI JOINT FABRIC SHALL BE EMBEDDED INTO 13-16 WET MILS (STANDARD FIELD APPLICATION THICKNESS) OF ENVIRO-DRI MEMBRANE ON THE SHEATHING/SUBSTRATE AND SUBSEQUENTLY COATED AND IMPREGNATED WITH 20 WET MILS OF ENVIRO-DRI MEMBRANE LEAVING A SMOOTH CONTINUOUS FILM THAT ALL BUT OBSCURES THE FABRIC TEXTURE.

The architecture, engineering, and design of the project using the Tremco products are the responsibility of the project's design professional. All products and systems must comply with local building codes and standards. This detail is for general information and guidance only and Tremco specifically disclaims any liability for the use of this detail. The project design professional determines, in its sole discretion, whether this detail or a functionally equivalent detail is best suited for the project. This detail is subject to change without notice. Contact Tremco to ensure you have the most recent version.

Enviro-Dri



Tremco Technical Support: 866-209-2404

Detail: Enviro-Dri System Notes

Drawn by: KAB

Checked by: JS

Scale: NTS

Date: 7/5/2022

File Name:

ED-Notes



Construction Products Group

www.tremcocpg.com