



# TECHNICAL DATA SHEET

## VULKEM® 360NF+/ 950NF/950NF

Elastomeric, Waterproof Traffic  
Deck Coating System

---

### PRODUCT DESCRIPTION

Vulkem® 360NF+/950NF/950NF is a modified polyurethane traffic deck coating system composed of a base coat (360NF+), heavy duty intermediate coat (950NF) and a top coat (950NF). This unique waterproofing system is designed to have tenacious adhesion, extreme impact and abrasion resistance along with remarkable chemical stability. The elastomeric properties of the system's components enable the complete assembly to give and work with the concrete slab, bridging the shrinkage cracks.

Vulkem® 360NF+ Base Coat is an enhanced, low-odor, low-VOC, water-cured urethane base coat designed to improve elongation, adhesion, and tensile strength over the original 360NF. It bonds firmly to clean, dry concrete and metal surfaces and maintains integrity with minor substrate movement or damage.

Vulkem 950NF Intermediate Coat is a low VOC, two-component urethane that is applied after the Vulkem 360NF+ Base Coat has cured.

The intermediate coat is loaded with aggregate to give the system excellent impact, abrasion and chemical resistance.

Vulkem 950NF Top Coat is a two-component polyurethane that is applied after the Vulkem 950NF intermediate coat has cured. Interlaminary adhesion to Vulkem 950NF is exceedingly strong. The top coat affords excellent abrasion resistance and chemical resistance to complete this Vulkem Traffic Deck Coating System.

---

### BASIC USES

Vulkem 360NF+/950NF/950NF is a cold-applied traffic deck coating system designed for waterproofing concrete slabs and protecting occupied areas underneath from water damage. Additionally, the system will protect the concrete from the damaging effects of water, deicing salts, chemicals, gasoline, oils and anti-freeze.

---

### FEATURES & BENEFITS

- Fast cure technology allows for same-day topcoating and return to service within 24 hours.
- Low odor and low VOC formulation is ideal for use in occupied or sensitive environments.
- **Enhanced tensile strength and elongation** improve crack bridging, impact resistance, and long-term performance.
- **Strong adhesion to concrete** without primer simplifies installation and reduces labor time.
- Mildew and fungus resistance safeguard concrete surfaces against environmental contaminants.
- Excellent durability and weather resistance extend the life of pedestrian and vehicular systems.
- Compatible with Tremco sealants and topcoats, supporting seamless integration into Vulkem traffic coating systems.

---

### AVAILABILITY

Immediately available from your local Tremco Sales Representative, Tremco Distributor or Tremco Warehouse.

---

### PACKAGING

Vulkem 360NF+: 5 gal (18.9 L) in a 6-gal (22.7-L) pail

Vulkem 950NF: Total of 4.2-gal kit – Part A 3.25 gal (12.3 L) in a 5-gal (18.9-L) pail, Part B 0.95 gal (3.6 L) in a 1-gal pail

---

### COLORS

Vulkem 950NF is available in Gray, Slate Gray, Black, Charcoal, \*White, \*Limestone, Beige, and \*Maple. Made-to-order and special colors also are available upon request.

\*Denotes special color.

---

## LIMITATIONS

- Do not apply to damp or contaminated surfaces.
- Use with adequate ventilation.
- Substrate must be at least 5 °F (3 °C) above the measured dew point temperatures to avoid dew point conditions.

---

## FIRE RATED ASSEMBLIES

ANSI/UL790 – Standard Test Methods for Fire Test of Roof Coverings  
CAN/ULC-S107 – Methods of Fire Tests of Roof Coverings

---

## APPLICABLE STANDARDS

Conforms to:

- ASTM C957
- CSA S413-14
- UL 790 - Class A Fire Rating for non-combustible substrates

---

## INSTALLATION

Concrete shall be water-cured and attain a 4000-psi minimum compressive strength. Concrete finish shall be a light steel trowel followed by a fine-hair broom, or equivalent ICRI #3/- #4 finish. Moisture content in the concrete must be lower than 4.5% as measured by a Tramex CME 4 Moisture Meter. Depending on concrete construction and job-site location, additional concrete testing may be required. Please contact your local Tremco Sales or Technical Representative.

Refer to the instructions for your specific system/application for installation details. The techniques involved may require modification to adjust to job-site conditions. Consult your Tremco Representative for specific design requirements.

---

## WARRANTY

A repair or replacement warranty is available on all Tremco products. Visit <https://www.tremcosealants.com/warranties/> for details.

Tremco Construction Products Group (CPG) brings together Tremco CPG Inc. and its Dryvit and Nudura brands; Willseal; Prebuck LLC; Tremco Barrier Solutions, Inc.; Weatherproofing Technologies, Inc. and its Pure Air Control Services and Canam Building Envelope Specialists offerings; and Weatherproofing Technologies Canada, Inc.



tremcosealants.com | 800.321.7906



Construction Products Group

3735 Green Rd. | Beachwood, OH 44122  
800.321.7906 | tremcocpg.com

## TYPICAL PHYSICAL PROPERTIES

| PROPERTY                          | TEST METHOD    | VULKEM 360NF+                                      | VULKEM 950NF                              | VULKEM 950NF                              |
|-----------------------------------|----------------|--|---|---|
| Flash Point                       | Set-A-Flash    | 204.8°F (96 °C)                                    | 200 °F (93 °C)                            | 200 °F (93 °C)                            |
| % Solids (by Weight)              | ASTM D1353     | 90%  | 99%                                       | 99%                                       |
| Drying Time @ 75 °F, 50% RH       | ASTM D1640     | 25-40 mil film, 6 to 12 hr                         | 12 mil film, 2 to 4 hr                    | 12 mil film, 2 to 4 hr                    |
| Open to vehicular traffic         |                | N/A  | 24 hr after cure                          | 24 hr after cure                          |
| Weathering                        | ASTM D822      | N/A  | N/A (indoor use only)                     | N/A (indoor use only)                     |
| Salt Spray                        | ASTM B117      | N/A  | No effect                                 | No effect                                 |
| Viscosity                         | Brookfield C&P | 8000 to 11000 cps                                  | 2000 cps                                  | 2000 cps                                  |
| Elongation                        | ASTM D412      | 550%   | 100%                                      | 100%                                      |
| Tensile Strength                  | ASTM D412      | 1015 psi   | 4200 psi                                  | 4200 psi                                  |
| Hardness (Shore A)                | ASTM D2240     | 50 to 70   | 75 (Shore D )                             | 75 (Shore D )                             |
| Adhesion (Peel Strength)          | ASTM D903      | Unprimed concrete, > 50 pli, 100% cohesive failure | 100% cohesive failure                     | 100% cohesive failure                     |
| Abrasion Resistance (1000 cycles) | ASTM D4060     | N/A  | N/A                                       | N/A                                       |
| Adhesion (Pull-Off)               | ASTM D4541     | 380 psi  | 70 mg                                     | 70 mg                                     |
| Accelerated Aging*                | ASTM D573      | No loss of elongation or tensile strength          | No loss of elongation or tensile strength | No loss of elongation or tensile strength |
| Tear Strength                     | ASTM D624      | N/A  | 270 pli                                   | 270 pli                                   |

\* Accelerated aging test. 1 daily cycle of UV and water spray greatly exceeds 1 day of real-world exposure. Contact Tremco Technical Service or your local sales representative for more information.

Please refer to our website at [www.tremcosealants.com](http://www.tremcosealants.com) for the most up-to-date Product Data Sheets.

NOTE: All Tremco Safety Data Sheets (SDS) are in alignment with the Globally Harmonized System of Classification and Labelling of Chemicals (GHS) requirements.

V360NFP950NF950NF-DS/0425

Tremco Construction Products Group (CPG) brings together Tremco CPG Inc. and its Dryvit and Nudura brands; Willseal; Prebuck LLC; Tremco Barrier Solutions, Inc.; Weatherproofing Technologies, Inc. and its Pure Air Control Services and Canam Building Envelope Specialists offerings; and Weatherproofing Technologies Canada, Inc.



[tremcosealants.com](http://tremcosealants.com) | 800.321.7906



Construction Products Group

3735 Green Rd. | Beachwood, OH 44122  
800.321.7906 | [tremcocpg.com](http://tremcocpg.com)