

TECHNICAL DATA SHEET

Vulkem[®] 360NF+/950NF

Low Odor/Fast Cure Indoor Pedestrian and Waterproofing System

PRODUCT DESCRIPTION

Vulkem[®] 360NF+/950NF is a composite waterproofing system comprised of tough-curing liquid polyurethane. It cures to form a rubber membrane surface that provides a lasting and easy-to-clean coating. Textured surfaces for pedestrian traffic will use an aggregate-laden top membrane to aid in wear and slip resistance. Vulkem 360NF+/950NF may be used to apply a seamless monolithic waterproof membrane to concrete, well-anchored AC plywood, and to primed metal surfaces.

Vulkem[®] 360NF+ Base Coat is an enhanced, low-odor, low-VOC, water-cured urethane base coat designed to improve elongation, adhesion, and tensile strength over the original 360NF. It bonds firmly to clean, dry concrete and metal surfaces and maintains integrity with minor substrate movement or damage.

Vulkem 950NF Top Coat is an aromatic, low VOC, two-component polyurethane, which when used in conjunction with the recommended aggregate, creates a tough, aesthetically appealing, skid resistant, wearing surface that forms a strong interlaminate bond to the Vulkem 360NF+ basecoat.

BASIC USES

Vulkem 360NF+/950NF is ideal for mechanical rooms and similar interior applications requiring an elastomeric waterproofing system.

SEALANT• WATERPROOFING & RESTORATION INSTITUTE Issued to: Tremco Incorporated Product: Vulkem 360 NF Basecoat & Vulkem 951 NF Topcoat ASTM D 412: Tensile Strength of Top Coat Vulkem 951 NF Topcoat Tensile Strength: 5,394 psi; Elongation: 294% Pass V ASTM D 4541: Adhesion of Base Coat Vulkem 360 NF Basecoat Pull-off Adhesion: 363 psi Pass 🖌 ASTM D 4060: Abrasion Resistance of Top Coat Vulkem 360 NF Basecoat Abrasion Resistance: 20 mgms loss - mgms loss/1,000 cycles Pass 🖌 Validation Date: 04/27/22 - 04/26/27 No. 422-VUL360 Copyright © 2022

DECK COATING VALIDATION www.swrionline.org

FEATURES & BENEFITS

- Fast cure technology allows for same-day topcoating and return to service within 24 hours.
- Low odor and low VOC formulation is ideal for use in occupied or sensitive environments.
- Enhanced tensile strength and elongation improve crack bridging, impact resistance, and long-term performance.
- Strong adhesion to concrete without primer simplifies installation and reduces labor time.
- Mildew and fungus resistance safeguard concrete surfaces against environmental contaminants.
- Excellent durability and weather resistance extend the life of pedestrian and vehicular systems.
- Compatible with Tremco sealants and topcoats, supporting seamless integration into Vulkem traffic coating systems.

AVAILABILITY

Immediately available from your local Tremco Sales Representative, Tremco Distributor or Tremco Warehouse.

PACKAGING

Vulkem 360NF+: 5 gal (18.9 L) in a 6-gal (22.7-L) pail Vulkem 950NF: Total of 4.2-gal kit – Part A 3.25 gal (12.3 L) in a 5-gal (18.9-L) pail, Part B 0.95 gal (3.6 L) in a 1-gal pail

COLORS

Vulkem 950NF is available in Gray, Slate Gray, Black, Charcoal, *White, *Limestone, Beige, and *Maple. Made-toorder and special colors also are available upon request.

*Denotes special color.

LIMITATIONS

- Do not apply to damp or contaminated surfaces.
- Use with adequate ventilation.
- Substrate must be at least 5 °F (3 °C) above the measured dew point temperatures to avoid dew point conditions.

FIRE RATED ASSEMBLIES

ANSI/UL790 – Standard Test Methods for Fire Test of Roof Coverings CAN/ULC-S107 – Methods of Fire Tests of Roof Coverings

APPLICABLE STANDARDS

Conforms to:

- ASTM C957
- CSA S413-14
- UL 790 Class A Fire Rating for non-combustible substrates

Tremco Construction Products Group (CPG) brings together Tremco CPG Inc. and its Dryvit and Nudura brands; Willseal; Prebuck LLC; Tremco Barrier Solutions, Inc.; Weatherproofing Technologies, Inc. and its Pure Air Control Services and Canam Building Envelope Specialists offerings; and Weatherproofing Technologies Canada, Inc.



tremcosealants.com 800.321.7906



3735 Green Rd. | Beachwood, OH 44122 800.321.7906 | tremcocpg.com

INSTALLATION

Concrete shall be water-cured and attain a 4000-psi minimum compressive strength. Concrete finish shall be a light steel trowel followed by a fine-hair broom, or equivalent ICRI #3/- #4 finish. Moisture content in the concrete must be lower than 4.5% as measured by a Tramex CME 4 Moisture Meter. Depending on concrete construction and job-site location, additional concrete testing may be required. Please contact your local Tremco Sales or Technical Representative.

Refer to the instructions for your specific system/application for installation details. The techniques involved may require modification to adjust to job-site conditions. Consult your Tremco Representative for specific design requirements.

WARRANTY

A repair or replacement warranty is available on all Tremco products. Visit https://www.tremcosealants.com/warranties/ for details.

Tremco Construction Products Group (CPG) brings together Tremco CPG Inc. and its Dryvit and Nudura brands; Willseal; Prebuck LLC; Tremco Barrier Solutions, Inc.; Weatherproofing Technologies, Inc. and its Pure Air Control Services and Canam Building Envelope Specialists offerings; and Weatherproofing Technologies Canada, Inc.



tremcosealants.com 800.321.7906



3735 Green Rd. | Beachwood, OH 44122 800.321.7906 | tremcocpg.com

TYPICAL PHYSICAL PROPERTIES			
PROPERTY	TEST METHOD	VULKEM 360NF+	VULKEM 950NF
Flash Point	Set-A-Flash	204.8°F (96 °C)	200 °F (93 °C)
% Solids (by Weight)	ASTM D1353	90%	99%
Drying Time @ 75 °F, 50% RH	ASTM D1640	25-40 mil film, 6 to 12 hr	12 mil film, 2 to 4 hr
Open to vehicular traffic		N/A	24 hr after cure
Weathering	ASTM D822	N/A	N/A (indoor use only)
Salt Spray	ASTM B117	N/A	No effect
Viscosity	Brookfield C&P	8000 to 11000 cps	2000 cps
Elongation	ASTM D412	550%	100%
Tensile Strength	ASTM D412	1015 psi	4200 psi
Hardness (Shore A)	ASTM D2240	50 to 70	75 (Shore D)
Adhesion (Peel Strength)	ASTM D903	Unprimed concrete, > 50 pli, 100% cohesive failure	100% cohesive failure
Abrasion Resistance (1000 cycles)	ASTM D4060	N/A	N/A
Adhesion (Pull-Off)	ASTM D4541	380 psi	70 mg
Accelerated Aging*	ASTM D573	No loss of elongation or tensile strength	No loss of elongation or tensile strength
Tear Strength	ASTM D624	N/A	270 pli

* Accelerated aging test. 1 daily cycle of UV and water spray greatly exceeds 1 day of real-world exposure. Contact Tremco Technical Service or your local sales representative for more information.

Please refer to our website at www.tremcosealants.com for the most up-to-date Product Data Sheets.

NOTE: All Tremco Safety Data Sheets (SDS) are in alignment with the Globally Harmonized System of Classification and Labelling of Chemicals (GHS) requirements.

V360NFP950NF-DS/0425

Tremco Construction Products Group (CPG) brings together Tremco CPG Inc. and its Dryvit and Nudura brands; Willseal; Prebuck LLC; Tremco Barrier Solutions, Inc.; Weatherproofing Technologies, Inc. and its Pure Air Control Services and Canam Building Envelope Specialists offerings; and Weatherproofing Technologies Canada, Inc.



tremcosealants.com 800.321.7906



3735 Green Rd. | Beachwood, OH 44122 800.321.7906 | tremcocpg.com